

AUIE00025 Intergrain Enviopro Endure 2 Pack Gloss

Introduction

Part A
701 W0219

Part B
701 W0222

Description and Image

Intergrain Enviopro Endure 2 Pack is an extremely durable, clear water based polyurethane for interior timber, parquet and cork floors. It can also be used to refresh Floating Floors. Endure 2 Pack is designed to maintain the natural colour of timber and is available in Matt, Satin and Gloss sheen levels. Endure 2 Pack uses cross-linking technology to provide resistance to abrasion, foot traffic, water, alcohol and mild chemicals, making it ideal for use in high traffic areas and commercial environments. Endure 2 Pack is low odour, quick drying (re-coat in 4 hours) and unlike oil based finishes, will not darken or yellow over time. ^Being water based, Endure 2 Pack emits significantly less VOCs (volatile organic compounds) into the atmosphere than traditional solvent based finishes and meets the VOC requirements of the GBCA. So, combined with being safer to use, Endure 2 pack is much gentler on the environment.

Green building compliant

The Green Building Council of Australia (GBCA) target for VOC level of floor coatings is less than 140 grams per litre of VOC. Endure 2 Pack can be used on Green Star Buildings as it emits significantly less VOCs than the target set by the GBCA. Refer to the datasheet on www.duspec.com.au for the actual VOC level of Endure 2 Pack.

Features and Benefits

- Extremely durable 2 pack polyurethane.
- Environmentally friendly.
- Water-based.
- Suitable for high traffic areas and commercial environments.
- Safer to use and gentle on the environment.
- Quick drying.

Uses

On interior timber and parquet floors. May be used on cork and floating floors in certain situations.

Precautions and Limitations

Do not apply in temperatures above 35°C or below 10°C. If using in temperatures above 30°C, Enviopro Wet Edge Extender can be added to Endure 2 Pack to a maximum of 5%, to ease application, follow instructions on the Wet Edge Extender label.

Performance Guide

Weather
Interior use only.

Heat Resistance
Up to 100C.

Water
Good for splashes and spillage.

Abrasion
Excellent.




Typical Properties

Gloss Level
>80% at 60°

Colour
Clear

Components
2

Number of Coats
2-3

Toxicity Non toxic		V.O.C. Level <135 g/L (Part A + Part B)	
Meets GBCA V.O.C. Requirements? Yes Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.			
Mixing Ratio 9:1			
Pot Life 3 hours		Touch Dry 1 hour	
Clean Up  Water			
Application Methods  Brush  Roller			
Application Conditions		Solids by Volume <input type="text" value="29"/>	
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	<input type="text" value="100"/>
Dry Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	<input type="text" value="29"/>
Recoat Time (min/hours)	<input type="text" value="4 hours"/>	<input type="text"/>	<input type="text"/>
Theoretical Spread Rate (m ² /L)	<input type="text"/>	<input type="text" value="10"/>	<input type="text" value="10"/>
Typical Property Notes Coverage 8 – 10m ² /L depending on the porosity of the timber. Dry times Dry times are based on drying conditions of 25°C and 50% relative humidity. Drying times will be longer in conditions cooler than 25°C or more humid than 50% humidity. Touch Dry 1 hour. Re-coat Allow a minimum of 4 hours drying between coats. Cold or humid conditions will require longer. Floors will take light foot traffic after 12 hours, and normal foot traffic after 72 hours. Full cure Allow 7 days.			

Application Guide

Surface Preparation

All surfaces must be clean, dry, free of wax, grease, dust and other contaminants. The presence of contaminants increases the possibility of rejection and delamination. Clean oily timbers such as Brushbox, Spotted Gum, Cypress and Tallowwood with methylated spirits and allow to dry. Prepare cork in accordance with cork manufacturer's specifications. If uneven, the surface should be sanded with coarse sandpaper. All nail holes and cracks

should be filled with Intergrain Woodblend™ putty, do not use Linseed Oil putty. Fine sand the floor finishing with 100 grit sandpaper, then with 150 mesh screen and vacuum thoroughly with a commercial grade vacuum cleaner to remove any sanding dust.

Application Procedure and Equipment

Mixing

Mix Endure 2 Pack Part A and Endure 2 Pack Part B at a ratio of 9 to 1 and shake for at least 2 minutes to ensure it is thoroughly combined. Strain product if required before use.

Pot life

3 hours, Endure 2 Pack must be used within 3 hours of mixing.

Application

It is recommended to shield doorways, fireplaces and windows from dust, dirt or other contaminants settling on the surface between coats, as this will affect the finished appearance. Do not completely seal, as adequate ventilation is required to assist with drying. Do not apply in temperatures above 35°C or below 10°C. If using in temperatures above 30°C, Enviropro Wet Edge Extender can be added to Endure 2 Pack to a maximum of 5%, to ease application, follow instructions on the Wet Edge Extender label.

New timber

Apply 1 coat of Enviropro Timberseal™ or Timberseal Ultra following the instructions on the label. Lightly sand Timberseal Ultra with a worn 180 mesh screen if needed. If using Timberseal, do not sand. Apply 2 coats of Endure 2 Pack using a 10mm nap microfibre roller. To improve adhesion and minimise grain raise, it is recommended to screen between coats with a worn 150 grit screen or 180 grit screen. To increase the wear resistance, apply 3 coats of Endure 2 Pack. On porous timbers, apply 3 coats of Endure 2 Pack to ensure a uniform finish.

Previously finished surfaces including Floating Floors

Wash the floor with Enviropro Squeaky Clean™ as per the label instructions. Sand to a dull finish with a 100 grit screen, vacuum thoroughly to remove dust, then wipe clean with a damp rag. To ensure adhesion, a test patch is recommended after the surface has been prepared. Apply a small test area with Endure 2 Pack, allow to dry for 24 hours then firmly press a strip of sticky tape over the coating and rip off quickly. If the coating is removed, sand the full surface back to bare timber. If the coating is not removed, sand the test area back to a dull finish. Apply 1-2 coats of Endure 2 Pack using a 10mm nap microfibre roller. If patches of the previous coating have worn back to expose bare timber, the full floor must be sanded back to bare timber, and product applied as per 'new timber' directions.

Slip resistance

Intergrain UltraGrip can be added to Endure 2 Pack Matt and Satin to achieve a more slip resistant finish. It is not recommended to add Intergrain UltraGrip to Endure 2 Pack Gloss as it will dull the gloss finish. For more information about system requirements refer to the datasheet on www.duspec.com.au. Add UltraGrip according to product instructions.

Health and Safety

SDS Number

DLXGHSEN001704 Endure 2 Pack Part A Gloss
DLXGHSEN001706 Endure 2 Pack Part B

SDS Link

https://go.lupinsys.com/duluxgroup/harms/public/materials/7bd8b64c7e823cd757070e51fc667db0-published/attachments_api/091292321d7c742c221cc0e342aaf180/se arch_api/ENVIROPRO_ENDURE_2_PACK_PART_A-AUS_GHS.pdf

Using Safety Precautions

Avoid contact with skin and eyes or breathing vapour and spray mist (dust). Wear waterproof gloves and safety glasses. Use only in well ventilated areas. Wash hands after use. Slippery when spilt; clean up immediately.

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage

Pack A

701 W0219

Size:

4.5L

Weight:

5kg

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.