

AUPP00016 Porter's Paints Stone Paint - Coarse

Introduction

Part A
PE1-LINE

Description and Image

Porter's Stone Paint Coarse has a coarsely textured finish similar to cement bagging that provides outstanding performance with the appearance of softness that comes with completely flat paints. Superior coverage, very low VOC, low odour, and an ultra-flat sheen level that hides surface imperfections and delivers perfect colour. Interior and Exterior use.

Features and Benefits

- High UV resistance
- Excellent Dirt pick-up resistance
- Low odour
- Low Volatile Organic Content (VOC)
- Meets the assessment criteria set by Ecospecifier™ and is therefore eligible for Green Star credits.
- Water wash up

Uses

Interior and exterior. Can be applied to most suitably prepared plasterboard, plaster, wood, masonry and previously painted surfaces.

✓ Interior ✓ Exterior ✓ Wall

Precautions and Limitations

Do not apply in high humidity, below 10°C or above 30°C.
A roller is not recommended for use with Stone Paint Coarse, as roller marks will be evident in the finished result.
Check colour before use.

Typical Properties			
Thinner Water			
Colour Available in a wide range of colors tinted from Standard, Mid, Deep, Clear, Red, Magenta and Black bases or ask our colourist for your own custom colour.			
Acrylic Range Base:			
Ultra Flat:	Eggshell:	Low Sheen:	Aqua Satin Enamel:
Aqua Gloss Enamel:	Stone Paint Fine:	Stone Paint Coarse: Standard Mid Deep Clear	
Components 1		Number of Coats 2	
V.O.C. Level <5g/L (untinted). Except Stone Paint Coarse Red base at <15 g/L(untinted)			
Touch Dry 1 hour (at 25 Deg C and 50% Relative Humidity)			
Clean Up  Water			
Clean Up Description Clean brushes and equipment with water. Do not pour paint down the drain. Disposal of empty paint containers via domestic recycling programs may differ between local authorities. Please confirm local requirements. For more information on responsible disposal of paint and packaging visit paintback.com.au or painttakeback.co.nz .			
Application Methods  Brush Stir thoroughly prior to use. Surface must be clean, dry and free from dust, oils and grease. For a natural cement-like appearance apply two coats by lime wash brush (4x14cm block brush) in a multi-directional manner. Recoat: 2 hours, allow more time in cooler or humid conditions. A roller is not recommended for use with Stone Paint Coarse, as roller marks will be evident in the finished result.			
Application Conditions	Solids by Volume		
	<input type="text" value="40"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	<input type="text" value="100"/>
Dry Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	<input type="text" value="40"/>
Recoat Time (min/hours)	<input type="text" value="2 hrs"/>	<input type="text" value="indefinite"/>	<input type="text" value="2 hrs"/>
Theoretical Spread Rate (m²/L)	<input type="text"/>	<input type="text"/>	<input type="text" value="10"/>

Application Guide

Surface Preparation

New/unpainted substrates:

Substrate should be a clean well-held surface free from loose material, dirt, grease, oil and mould. Dust down before proceeding.

On new unpainted plasterboard sheeting, render, brick or timber, spot prime all joints and repaired areas with Porter's Prepare & Prime, then apply two coats of same to entire area.

On new unpainted fresh set plaster do not proceed until plaster has thoroughly set and has dried completely. Firstly, apply 1 coat Porter's Mineral Silicate Primer by brush or roller. Touch dry 20 minutes. Allow 2 hours dry time. Then apply by brush, roller or spray 1 coat Porter's Prepare & Prime.

Previously painted substrates:

Provided the surface is clean and sound, Porter's Stone Paint is self-priming and can be applied directly over previously painted surfaces. (Except oil-based paints or polyurethanes). High gloss paints or varnishes should be sanded to remove gloss and create a "keyed" surface.

Surfaces painted with oil-based paints, or previously painted surfaces with loose, peeling or flaking paint must be made sound by scraping off loose paint. Fill nail holes and cracks with suitable filler, sand and dust off. Spot prime all joints and repaired areas with Porter's Prepare & Prime, then apply one coat to entire area.

Application Procedure and Equipment

Do not apply paint if Relative Humidity is above 85% or temperature is within 3°C of Dew Point.

Do not apply if the surface temperature is greater than 30°C or below 10°C, or likely to fall below 10°C during the application or drying period.

Stir thoroughly prior to use. Surface must be clean, dry and free from dust, oils and grease. For a natural cement-like appearance apply two coats by lime wash brush (4x14cm block brush) in a multi-directional manner. Recoat: 2 hours, allow more time in cooler or humid conditions.

A roller is not recommended for use with Stone Paint Coarse, as roller marks will be evident in the finished result.

Health and Safety

SDS Number

DLXGHCEN002533

SDS Link

[View SDS Link](#)

Using Safety Precautions

Keep out of reach of children. Use only in well ventilated areas.

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage

Pack A

PE1-LINE

Size:

1L, 4L, 10L & 15L

Weight:

1.72kg, 6.67kg, 16.27kg & 24.31kg

Flash Point

NA

UN Number

NA

Dangerous Goods Class

Not classified as Dangerous Goods for transport by Road & Rail and Marine, Not classified as Dangerous Goods for transport by Air.

Package Group

NA

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.