

AUDU00123 Dulux Precision All Metal Primer

Introduction

Part A
51W89937

Description and Image

Dulux Precision All Metal Primer is a water based primer designed for metal surfaces† including galvanised iron, Zinalume®, wrought iron, steel, aluminium, copper, brass and stainless steel. Dulux Precision All Metal Primer has been formulated with anti-corrosive pigments to inhibit rust and corrosion for the protection of metal surfaces.



Features and Benefits

- Contains anti corrosive pigments.
- Water Based.
- Excellent adhesion.
- Can be over coated with water based and solvent based topcoats
- Inhibits rust and corrosion.
- Easy clean up after use
- Bonds directly to most metal substrates
- Fast drying.
- Low odour.

Uses

Suitable for interior & exterior use.
Suitable for Galvanised iron, Zinalume, aluminium, steel, wrought iron, copper, brass and stainless steel.
This product is suitable for non structural use only.
Suitable for use under Dulux topcoats.

✓ Interior ✓ Exterior

Precautions and Limitations

Dulux Precision All Metal Primer is not suitable for use on Structural, Infrastructure, Commercial or Industrial fabrications. For Structural, Infrastructure, Commercial and Industrial fabrications Dulux recommends standard AS/NZS 2312 (as updated) be followed using the appropriate Dulux Protective Coatings products.

Do not paint at temperatures at or below 10°C or when the temperature may fall below 10°C during the drying period. Rain or dew will damage the film during the drying period.

Whilst this product is lead free, it contains dispersants and inhibitors which will affect drinking water. When priming roofs used for collection of drinking water, disconnect run off pipes until the primer has been coated with an appropriate Dulux Roofing Coating.

DO NOT TINT

Performance Guide

Weather Excellent weather resistance as a part of system.	Salt Good resistance as part of a system
Heat Resistance Excellent resistance to usual exterior exposed surface temperatures.	Water Excellent resistance to rain and condensation for prolonged periods as part of system.
Solvent Sensitive to aromatic hydrocarbons and alcohol. Excellent when top-coated.	Abrasion Not applicable.
Acid Not applicable	Alkali Not Applicable

Typical Properties

Gloss Level Low Sheen	Thinner Water
Colour Grey	
Components 1	Number of Coats 1
Toxicity Lead free but contains dispersants and inhibitors which will affect drinking water	V.O.C. Level <60g/L
Shelf Life 2 years	Meets GBCA V.O.C. Requirements? Yes Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.
Sanding Properties Sandable after 2 hours	Mixing Ratio Not Applicable
Touch Dry 20 Minutes.	
Clean Up  Water	

Use Xylene to clean up dry product from equipment.			
Clean Up Description Clean all equipment with water before the product starts to film form			
Application Methods			
Air Spray Airless Spray Brush Roller			
Application Conditions	Solids by Volume		
	<input type="text" value="37"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="68"/>	<input type="text" value="136"/>	<input type="text" value="68"/>
Dry Film Per Coat (microns)	<input type="text" value="25"/>	<input type="text" value="50"/>	<input type="text" value="25"/>
Recoat Time (min/hours)	<input type="text" value="2 hours"/>	<input type="text" value="Indefinite"/>	<input type="text" value="2 hours"/>
Theoretical Spread Rate (m ² /L)	<input type="text" value="14.80"/>	<input type="text" value="7.40"/>	<input type="text" value="14.80"/>

Application Guide

Surface Preparation

Prepainted surfaces: Ensure any loose and flaking paint (see Note 1.) is scraped off. Sand all surfaces to a flat finish. Dust off. Treat any bare metal as indicated below.

Please Note:

1. Check the adhesion of the old paint by cutting an 'X' through the film with a razor blade or trimming knife, pressing cellulose tape firmly across the cut and ripping it off. If the old paint comes off with the tape it should all be removed.
2. Dulux Precision All Metal Primer is suitable for use on substrates that have been sand blasted. (Be mindful that this product is not suitable for commercial, industrial or infrastructure use where most sand blasted metal surfaces are likely to be present.)
3. For commercial & industrial fabrications Dulux recommends standard AS/NZS 2312 (as updated) be followed using the appropriate **Dulux Protective Coatings products**.

Metal surfaces this product can be used:

Galvanised iron: Clean with Scotch Brite and mild detergent solution. Rinse off thoroughly.

Galvanised iron (aged): Remove white rust by wire brushing or scraping. Wipe surface clean with mineral turps to remove rust, grease, oils and dirt. Allow to dry.

Zincalume, Copper, Brass & Stainless Steel: Clean with mild detergent solution. Rinse off thoroughly.

Zincalume (aged): Remove white rust by wire brushing or scraping. Clean with mild detergent solution. Rinse off thoroughly.

Colorbond prepainted steel (Aged): Ensure surface is sound by performing an adhesion test. Any loose or flaking paint needs to be removed. Spot prime bare areas with 1 coat of Dulux Precision All Metal Primer.

Steel/wrought iron (new): Wipe surface with mineral turps to remove residual rust, grease, oil and dirt. Allow to dry.

Steel/wrought iron (rusted) : Remove rust scale by scaping, sanding or wire brushing. Wipe surface with mineral turps to remove residual rust, grease, oil and dirt. Allow to dry. (Make sure that all rust is removed)

For more corrosive environments (within 2 km of the coast) apply a base coat of Dulux Metalshield Cold Galv Primer to any wrought iron or mild steel components including nail heads.

- Application Procedure and Equipment
- Brush, roller, conventional and airless spray
 - Stir contents thoroughly before and during use with a broad, flat stirrer using an upward lifting action.
 - Brush/Roller: Apply full even coats to the prepared surface.

- Conventional/Airless Spray: Suitable for application by conventional or airless spray equipment. If necessary thin with up to 50ml/litre of water.
- For Galvanised Iron, Zinalume, Aluminium, Copper, Brass and Stainless Steel apply one coat of Dulux Precision All Metal Primer.
- For Steel & Wrought Iron apply two coats of Dulux PRECISION All Metal Primer.
- Note: Thinning can reduce the rust inhibiting performance of Dulux Precision All Metal Primer
- **DO NOT TINT**

Health and Safety	
SDS Number DLXGHSEN001852	SDS Link View SDS Link
Using Safety Precautions Keep out of reach of children. Avoid contact with skin and eyes or breathing vapour and spray mist. Wear waterproof gloves and safety glasses. Use only in well ventilated areas. Wash hands after use.	
Please refer to SDS Link. In case of emergency, please call 1800 220 770.	

Transport and Storage	
Pack A 51W-89937	
Size: <input type="text" value="1 Litre 4 Litre"/>	Weight: <input type="text" value="1.5 Kg 5.7 Kg"/>
Flash Point Not Applicable - Water Based	UN Number NOT APPLICABLE
Dangerous Goods Class Not Classified as Dangerous Goods	Package Group Not classified as Dangerous Goods

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.