

AUPP00026 Porter's Paints Clearcote

Introduction

Part A
PZ5-D0842

Description and Image

Porter's Clearcote is a low odour, fast drying, water-based clear finish suitable for a variety of interior and exterior surfaces. Porter's Clearcote has excellent UV stability and resists yellowing.

Features and Benefits

- Water based.
- Low Odour.
- Fast drying.
- Dries to a low lustre finish.
- Has excellent UV stability.
- High resistance to yellowing.

Uses

Suitable for use on a wide variety of substrates, including any interior timber that requires sealing and protection. Ideal for interior wooden or concrete floors, furniture and, kitchen cupboards.

✓ Interior

Precautions and Limitations

Not suitable for use over Porter's Milk Paint, Porter's Fresco or previously oiled timbers or timbers that are oily in nature*. Not suitable on exterior timber surfaces.

Kitchen and bathroom bench tops: May be subject to staining if used on timber bench tops where there will be heavy soiling from oil, food and make up.

Not recommended as a sealer for floor tiles as they may become slippery when wet.

Important information about damp substrates: Concrete slabs can be affected by condensation, moisture migration through the concrete from the soil underneath, broken or leaking pipes under the concrete, surface water leaks or flooding. Wooden interior floors can be affected by flooding, improper cleaning, cracks in foundations, or liquid spills. All these scenarios are the enemy of paints and clear coatings, and all sources of dampness (hydrostatic pressure), not only on the surface, but through the entire substrate, must be eliminated and the substrate thoroughly dried throughout prior to applying Clearcote. Applying Clearcote onto a damp substrate will prevent film cure, and will cause the Clearcote to appear cloudy and delaminate (peel off).

Test before use on timber with a high tannin content. Normally tannin bleed is undetectable, but if you are using Clearcote over a finish such as Wood Wash tannin bleed may be visible as a slight brown staining. Tannin bleed does not affect product performance. Porter's Tannin Block should be considered to prevent this problem, and should be applied over the Wood Wash, and prior to application of Clearcote.

*Important information about timber:

Not suitable for use over timbers that are oily in nature, such as brush box, blackbutt, jarrah, spotted gum, teak and other hardwoods that have a natural oiliness or waxiness. These timbers should be well aged and allowed to dry out to allow the Clearcote to penetrate, otherwise the natural oils in the timber will repel the water-based Clearcote causing lack of adhesion, resulting in peeling and delamination.

Not suitable for exterior decking, due to the high oil content in decking timbers. refer to our website for a more suitable product.

Always test prior to use. Do not apply in high humidity, below 10°C or above 30°C. Note that this also applies to the surface temperature of the substrate. If applied to a surface that is hot from the sun, Clearcote may dry too fast and not cure correctly and this may result in loss of adhesion, cracking and therefore allow the ingress of moisture.

Not suitable for spraying.

Typical Properties			
Colour Appears milky white in can, dries clear.			
Components 1		Number of Coats 2	
V.O.C. Level < 29 g/L			
Touch Dry 30 minutes (at 25 Deg C and 50% relative Humidity)			
Clean Up Water			
Clean Up Description Clean brushes and equipment with water. Do not pour paint down the drain. Disposal of empty paint containers via domestic recycling programs may differ between local authorities. Please confirm local requirements. For more information on responsible disposal of paint and packaging visit paintback.com.au or painttakeback.co.nz .			
Application Methods Brush Pad lamb's' wool applicator (recommended for floors). Not suitable for spraying.			
Application Conditions	Solids by Volume <input type="text" value="29"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	<input type="text" value="67"/>
Dry Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	<input type="text" value="19"/>
Recoat Time (min/hours)	<input type="text"/>	<input type="text"/>	<input type="text" value="2 hours"/>
Theoretical Spread Rate (m ² /L)	<input type="text"/>	<input type="text"/>	<input type="text" value="15"/>
Typical Property Notes Covers approximately 15m ² per litre, depending upon porosity, surface texture and wastage rates.			

Application Guide

Surface Preparation

The substrate should be a clean well-held surface free from loose material, dirt, dust, grease, oil and mould. Dust down before proceeding. Allow all paints and finishes to a dry a minimum of 72 hours prior to the application of Porter's Clearcote. When being applied as a floor sealer, vacuum prior to application.

COMPLEMENTARY PRODUCTS:

Porter's Clearcote is compatible for use over Porter's Wood Wash and Porter's Concrete Wash. Test before use as a slight colour variation may occur.

Application Procedure and Equipment

Do not apply paint if Relative Humidity is above 85% or temperature is within 3°C of Dew Point.

Do not apply if the surface temperature is greater than 30°C or below 10°C, or likely to fall below 10°C during the application or drying period.

Stir thoroughly prior to use. Apply two coats by brush or lambs' wool applicator (recommended for floors). Touch dry in 30 minutes. Allow minimum 2 hours dry time between coats. Hard dry in 2 hours. Sand lightly between coats to remove any raised grain. Vacuum to remove dust before applying another coat. Allow 4-6 hours before allowing light foot traffic on floor surfaces. Full cure is achieved in 2 days. On exterior surfaces protect from rain for 3 days. Not suitable for spraying.

Health and Safety

SDS Number

DLXGHCEN001310

SDS Link

[View SDS Link](#)

Using Safety Precautions

Keep out of reach of children. Use only in well ventilated areas.

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage

Pack A

PZ5-D0842

Size:

1 litre, 4 litre, 10 litre & 15 litre

Weight:

1.18 Kg, 4.53 Kg, 10.93 Kg, 16.3 Kg

Flash Point

NA

UN Number

NA

Dangerous Goods Class

Not classified as Dangerous Goods for transport by Road & Rail and Marine, Not classified as Dangerous Goods for transport by Air.

Package Group

NA

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.