

AUAV00016 Dulux Avista Concrete Sealer Tintable Base Semi Gloss

Introduction

Product Code
FD278063-19L

Product Overview and Image

Dulux Avista Concrete Sealer Tintable Base is to be mixed with Dulux Avista Concrete Sealer Colour Tint to provide a protective coloured coating to re-colour or refresh most concrete surfaces.

Product Category
Concrete Sealer







Features and Benefits

- Colours & protects external concrete surfaces from dirt ingress
- Semi Gloss finish
- Available in 20 colours
- Easy to apply
- No primer required

Uses

Dulux Avista Concrete Sealer Tintable Base can be used on most types of exterior concrete surfaces including concrete pavers* and stamped, stencilled, plain, coloured and resurfaced concrete. It is not recommended for use on internal concrete floors. Caution: this product is not recommended for use on smooth or steep concrete surfaces as it may cause the surface to become slippery, particularly when wet.

* Pavers on a sand or gravel base may experience delamination due to rising moisture.

Typical Properties			
Components 2		Mixing Ratio 19L Base, 1L colour Tint	
Shelf Life > 4 years from Date of Manufacture when stored in unopened containers in a cool dry environment		Pot Life Not Applicable. Tint is for colour purposes only, not chemical curing.	
Yield 20L		V.O.C. Content 689 grams per litre	
Clean Up Dulux Avista Solvent			
Sizes 19L			
Meets GBCA V.O.C. Requirements? No			
Application Methods <div>  Air Spray  Brush  Roller  Broom </div>			
Specifications		Solids by Volume	
		<input type="text" value="21"/>	
		Min	Max
Wet Film Per Coat (microns)	<input type="text" value="80"/>	<input type="text" value="150"/>	Recommended <input type="text" value="120"/>
Dry Film Per Coat (microns)	<input type="text" value="40"/>	<input type="text" value="80"/>	<input type="text" value="60"/>
Theoretical Spread Rate (m ² /L)	<input type="text" value="3"/>	<input type="text" value="6"/>	<input type="text" value="4"/>
Drying Time			
		Min	Max
Touch Dry (min)	<input type="text" value="60"/>	<input type="text" value="12"/>	Recommended <input type="text" value="120"/>
Recoat Time (min/hours)	<input type="text"/>	<input type="text"/>	<input type="text" value="2 hours"/>
Comments	<input type="text" value="Full cure 5 days"/>		

Product Properties	
UV Resistance Very good resistance	Water Water Resistant to water including intermittent ponded water from rain or washing events
Sodium Hydroxide (Alkali) No visual effect	Sulphuric Acid No visual effect
Sodium Hypochlorite (Pool Chlorine) No visual effect	Petrol (Regular Unleaded) Softening and dulling of surface - immediately clean with detergent and when dry treat with Dulux Avista Solvent. Resealing may be required.
Engine Oil No visual effect	Brake Fluid (Dot 3) Softening and dulling of surface - immediately clean with detergent and when dry treat with Dulux Avista Solvent. Resealing may be required.
Distillate No visual effect	Methylated Spirits Softening with white discolouration - immediately clean with detergent and when dry treat with Dulux Avista Solvent. Resealing may be required.
Sodium Chloride (Salt) No visual effect	

Slip Rating			
Surface Finish	Finish Coat	Slip Reducing Additive	Result
Steel Trowel finished concrete	Dulux Avista Tintable Sealer Semi-Gloss	No	P2
Steel Trowel finished concrete	Dulux Avista Tintable Sealer Semi-Gloss	Dulux Avista Slip Reducing Additive Powder	P4
Steel Trowel finished concrete	Dulux Avista Tintable Sealer Semi-Gloss	Dulux Avista Slip Reducing Crushed Glass	P5
Coved finished concrete	Dulux Avista Tintable Sealer Semi-Gloss	No	P4

Maintenances
<p>Surface should be cleaned regularly, removing mud, dirt & gravel by sweeping and/or pressure cleaning.</p> <p>Remove oil, grease and other chemicals contaminants immediately.</p> <p>Remove excess leaf & organic matter to avoid staining.</p> <p>Avoid driving on surface with rocks in tyres.</p> <p>Dulux Avista Concrete Sealer Coloured should be resealed approximately every 2 years. *</p> <p>*Actual lifespan of the product may vary depending on frequency of use & environmental factors.</p>

Application Guide

Surface Preparation

Preparation Instructions for New Cured and Old Concrete (unsealed)

Ensure concrete is sufficiently cured (recommended minimum 14 days).

Concrete is to be clean and free of grease, oil, paint or any curing agent. Stiff broom and general purpose cleaner recommended. Any oil stains should be treated & cleaned with an industrial degreaser.

Pressure clean surface at minimum 2000 psi and allow to dry.

Acid etch with hydrochloric acid. Dilute approximately 20 parts water to 1 part acid (depending on porosity) to remove any loosely bound cement and laitance.

Note: smooth concrete will require a higher acid content. Maximum strength - 10 parts water to 1 part acid.

Apply diluted acid to surface using a large head watering can, applying in a criss cross motion (approximately 5-10m² sections). Acid will start to fizz on the surface once it starts to react with the laitance in the concrete. Pressure clean immediately to clean and remove all remnants of acid (do not allow acid to dry on surface). Pressure clean at minimum 2000 psi. Allow surface to dry before sealing (sealing over damp concrete will cause whitening).

Preparation Instructions for Sealed Concrete

A cross hatch test is required if the surface has been sealed more than 2 years ago to ascertain whether existing sealer is suitable to be resealed over.

1. Use a sharp blade to create a light "cross-hatch" incision through the sealer.
2. Place a piece of self adhesive tape (suggest clear packing tape) over the incision.
3. Press firmly for maximum adhesion and remove sharply. Repeat with fresh tape several times.

If sealer is present on the tape, it is advised the sealer be completely stripped from surface. Seek professional contractors should stripping be required.

If there is no sign of sealer adhering to the tape or delaminating from the surface, this would indicate that the bond of the existing sealer is sufficient for resealing.

Important note: if current sealer shows signs of whitening or blooming, regardless of cross hatch test results, sealer may need to be stripped completely from the surface. Whitening may reoccur if new coat of sealer is applied over this problem.

Cleaning

Concrete is to be clean and free of grease and oil. Stiff broom and general purpose cleaner recommended. Any oil stains should be treated & cleaned with an industrial degreaser.

Pressure clean at minimum 2000 psi to clean and remove all contaminants. Allow surface to dry before resealing (sealing over damp concrete will cause whitening). Moisture content must be below 10%.

Solvent Treatment

If over coating an **existing clear sealer**, solvent is required to reactivate the existing sealer. This will help with the adhesion of the new sealer coat. Apply Dulux Avista Solvent to the area being resealed using a roller and roller tray.

Note: If resealing a resurfaced area, DO NOT apply too much solvent as it may soften the resurfacing product. Complete solvent treatment of entire surface. Allow area to dry enough to walk on before proceeding to the next stage.

Application Procedure and Equipment

Mixing in colour tint

Stir Dulux Avista Sealer Tint well before adding to base.

Add 1 x sealer tint to tintable base, stirring thoroughly with paint stirrer or mixing paddle until colour is uniform (approx. 1 minute).

First coat may be thinned up to 20% with Dulux Avista Solvent if required (new or aged uncoated surfaces only).

Application Methods

Sealer to be applied by a suitable solvent resistant broom or 11mm-22mm nap roller. Roller used will depend on the profile of the concrete.

The sealer must be mixed regularly during application to ensure colour consistency.

To apply sealer, pour sealer into a roller tray, and evenly roll or broom onto the surface.

Ensure sealer is not applied too thick and no pooling occurs as bubbling can occur.

Avoid excess sealer build up on the edges of the roller. This can lead to roller lines in the surface.

If required, an additional coat of sealer can be applied after a minimum of 2 hours, (recommended recoat 2 hours)

Drying time: Minimum of 2 hours between coats when applied at 25°C and above at 50% relative humidity. Recoat times will be longer in cooler weather (<25°C) or higher humidity.

Do not apply sealer at temperatures below 8°C or above 35°C.

To obtain an increased slip resistance it is advisable to use the appropriate Slip Reducing Additive with the sealer for better grip under adverse conditions e.g. wet areas, steep slopes and pool surround areas.

Health and Safety

SDS Number
PARGHSEN000581

SDS Link
[View SDS Link](#)

Using Safety Precautions

Flammable liquid and vapour. May be fatal if swallowed and enters airways. Harmful in contact with skin. Causes skin irritation. Causes serious eye irritation. Harmful if inhaled. May cause respiratory irritation. May cause damage to organs through prolonged or repeated exposure

Recommended PPE:

Organic vapour respirator mask
Solvent resistant gloves
Safety eye wear
Appropriate solvent and acid resistant foot wear

Storage conditions:

Store in a well-ventilated place. Keep cool. Keep container tightly closed. Store locked up. Refer to SDS.

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Precautions and Limitations

The sealed surface should not have foot traffic for at least 24 hours and vehicle traffic for at least 5 days.

Do not seal in high winds or if rain is likely.

Do not apply over painted surfaces. Paint removal required.

Application of sealer can lower slip resistance (slip resistance additives available).

Not recommended for internal areas, including garage floors.

Not suitable for food preparation areas.

Not a waterproofing membrane.

Do not seal at temperatures below 8°C or above 30°C.

Important note: Surfaces with a slope of 1:8 (1 metre fall across 8 metres of distance) or greater are not recommended for coating, even with the addition of Dulux Avista Slip Reducing Additive. Contact Dulux Avista for further advice on sloped surfaces.

Transport and Storage

Line Shade /Pack A

FD278051 DULUX AVISTA SEALER TINTABLE BASE

Size:

Weight:

19L

21kg

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.