

AUPR00009 Dulux Professional Polyurethane Matt

Introduction

Part A
394-84184

Description and Image

Dulux Professional Polyurethane Quick Dry Matt is an interior quick drying tough polyurethane clear which dries to a hard uniform flat finish. Excellent mar resistance properties.

Features and Benefits

- Attractive flat finish
- Quick drying
- Mar resistant
- One pack
- Highlights the natural timber look, an attractive subtle matt finish.
- Polyurethanes dry faster than varnishes. Saves time between coats.
- Tougher & longer wearing than a varnish or French polish.
- No messy mixing two cans, no limited pot life. Saves time & no wastage

Uses

Dulux Professional Polyurethane Quick Dry Matt is an attractive, mar resistant, flat finish on furniture, doors, skirtings, handrails, timber panelling and cork tiles. It is not recommended for floors.

Precautions and Limitations

All preparation and painting must conform to AS2311: The Painting of Buildings.





Do not apply if the surface temperature is below 10C or conditions indicate it will fall below 10C during the drying period.

If the temperature falls towards 10C or if the humidity is high, ensure air circulation is adequate by opening a window and using a fan.

Not suitable for use on floors.

Performance Guide

Weather For interior use only, not recommended for exterior use.	Salt Good resistance to salt splash
Heat Resistance Up to 120C. Premature yellowing and embrittlement if film subjected to continuous heat.	Water Good resistance to water splash.
Solvent Resists alcohol and hydrocarbons. Film is liable to attack from other strong solvents.	Abrasion Moderate resistance to abrasion.
Acid Suitable for dilute splash	Alkali Suitable for dilute splash

Typical Properties			
Gloss Level 5-15 at 60 degrees	Thinner Mineral Turpentine		
Colour Clear when dry, but appears milky in the can.			
Components 1	Number of Coats 3		
Toxicity Lead free. Dry film is non-toxic and conforms to AS1647, Part 3.	V.O.C. Level < 450g/L untinted		
Touch Dry 2 Hours			
Clean Up  Thinner			
Clean Up Description Clean all equipment with mineral turpentine.			
Application Methods  Airless Spray  Brush  Roller			
Application Conditions	Solids by Volume		
	<input type="text" value="43"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="62"/>	<input type="text" value="62"/>	<input type="text" value="62"/>
Dry Film Per Coat (microns)	<input type="text" value="27"/>	<input type="text" value="27"/>	<input type="text" value="27"/>
Recoat Time (min/hours)	<input type="text" value="6 Hours"/>	<input type="text" value="Indefinite"/>	<input type="text"/>
Theoretical Spread Rate (m ² /L)	<input type="text" value="16"/>	<input type="text" value="16"/>	<input type="text" value="16"/>

Application Guide

Surface Preparation

Surfaces must be clean, dry and completely free from wax, floor polishes, etc. Surfaces previously painted with clear must be thoroughly sanded in direction of the grain to remove all traces of gloss. Fill all nail holes and cracks and sandpaper smooth in the direction of the grain, dust off with a soft clean cloth. For a superfine finish, fill open grained timber with a suitable filler. Stain bare timber surfaces if required with an interior stain.

For best results, seal timber grain with one coat of Dulux Professional Prepcoat Sanding Sealer before finishing coats.

Application Procedure and Equipment

Brush, roller, conventional or airless spray

Stir thoroughly with a broad flat stirrer, using an upward lifting action.

Brush/Roller

For a fine finish apply by brush or spray.

Airless/Conventional Spray

Suitable for application by all standard spray equipment. If necessary thin with spraying thinner with up to 30 ml per litre for airless and 100 ml per litre for conventional spray.

Health and Safety

SDS Number
36612, 0

SDS Link
[View SDS Link](#)

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage

Pack A
394-84184

Size:

4 Litre

Weight:

4.3 Kg

Flash Point
>23C

UN Number
1263

Dangerous Goods Class
3

Package Group
III

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.