

AUDU00102 Dulux Texture Primer Low Sheen

Introduction

Part A
195-85719

Approvals
N/A

Description and Image

Dulux Textured Primer is a high build, primer-sealer for exterior use on porous masonry under the Dulux Exterior Texture Cover range. Applied by conventional nap roller, a fine aggregate fills masonry pores and minor imperfections providing a sealed anti-slip textured surface which greatly assists the application of subsequent texture coats.

Features and Benefits




- Anti-Slip Precoat
- Fills and Covers imperfections
- Water Based
- Aids application of Dulux texture Coats
- High Build Acrylic
- easy application and economical clean up

Uses

Dulux Texture Primer is a Water Based Acrylic primer-sealer for masonry substrates to unify the substrates porosity, it ensures maximum adhesion, slip resistance and to provide excellent key for subsequent texture coatings.

Performance Guide

Weather Excellent - enhances system durability	Salt Resists migration of soluble salts
Heat Resistance N/A - not tested	Water Highly water resistant
Solvent N/A - not tested	Abrasion N/A - not tested
Acid N/A - not tested	Alkali Excellent Alkali Resistance

Typical Properties			
Gloss Level Low Sheen	Thinner Not Recommended		
Colour White			
Number of Coats One			
V.O.C. Level 20.2			
Touch Dry 1 hour			
Clean Up			
 Water			
Clean up water DO NOT THIN			
Application Methods			
 Brush  Roller			
Application Conditions	Solids by Volume		
	<input type="text" value="42.3"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="400"/>	<input type="text" value="254"/>	<input type="text" value="254"/>
Dry Film Per Coat (microns)	<input type="text" value="169"/>	<input type="text" value="107"/>	<input type="text" value="107"/>
Recoat Time (min/hours)	<input type="text" value="4 Hrs"/>	<input type="text"/>	<input type="text"/>
Theoretical Spread Rate (m ² /L)	<input type="text" value="3.2"/>	<input type="text" value="4"/>	<input type="text" value="4"/>

Application Guide

Surface Preparation

General (all surfaces)

Treat mould, moss and algae prior to other surface preparation.

Wash with a bleach solution and/or de-mossing chemical then rinse with fresh water. Efflorescence on masonry (white crystalline deposits) should be removed by dry brushing with a stiff brush then wipe down the surface with a 5% solution of acetic acid (white vinegar). Thoroughly wash all surfaces with a mild detergent. Rinse with fresh water and allow to dry.

Previously Painted Surfaces

(1) Remove all loose or peeling paint. Test if previous coatings are in sound condition by cutting a small X through the existing paint with a sharp blade. Press cellulose tape firmly against the cut and then rip off. If paint comes off it is unsound and should be removed. Repeat in a number of areas to test. Wash down and sand all painted areas.

(2) Fill any cracks or holes with a suitable exterior grade filler. Sand all surfaces to a flat finish.

Bare or Unpainted Surfaces

Brick: Suitable over porous brick. Glazed terracotta bricks or unevenly laid bricks may not be suitable for coating. Test areas are recommended.

Cement Render: New cement render should be allowed to cure for 28 days prior to coating. "Block down" with a brick or masonry rubbing stone to remove any loose surface sand, and then broom.

Fibre Cement (FC): Refer to FC manufacturer regarding safety for handling and working with fibre cement. Do not sand or cut asbestos cement. Ensure nails and screws are non-corrosive. Flush joint recessed edge FC with a suitable jointing system according to FC manufacturer recommendations.

Helpful hints

Masking

Application of any heavy bodied texture coating requires protection and masking of adjoining surfaces.

Use a good quality external grade masking tape. Mask ground areas with disposable plastic drop sheets. When job is completed remove masking tape before material sets.

Thoroughly dust down all floor and pavement areas before masking to ensure masking tape adheres.

Application Procedure and Equipment

Refer to the Dulux website for a step-by-step application guide and tips on applying Dulux Exterior Texture Primer.

Stirring: Stir well with a broad flat paddle using an up and down scooping motion.

Cutting in: Using a brush, apply sparingly to edges, internal angles and areas not accessible with a roller. Finish brushed areas with a "dabbing" motion and feather out. Do not leave thick straight edge lines as these will be visible after roller application. Alternatively, working in a team apply broad wall areas by roller, up to edges, allowing a partner to "dab" in edges whilst still wet.

Roller application: Generously load the roller and apply from the ground upwards in vertical strips.

TIP: The first few strips applied will essentially only fill the roller, with less material applied to the wall. Work these strips well to thoroughly wet out the roller. Successive strips will deliver more material to the wall

Apply the material in strips of approximately ½ –1m in length. Reload roller after each strip and repeat until a manageable section has been "delivered" (approximately 3 – 4 strips wide).

Spread the material evenly by rolling diagonally across the surface.

Apply a fresh strip of wet material to create a "working wet edge", then "lay-off"

Health and Safety

SDS Number

23026

SDS Link

[View SDS Link](#)

Using Safety Precautions

For detailed information refer to the product label and the current Material Safety data Sheet available through Dulux Sales and Customer service Offices 132377 AUS.

Ensure adequate ventilation.

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage	
Pack A 195-85719	
Size: 4 litre, 10 litre	Weight: 5.3 Kg 12.9 Kg
Flash Point NA	UN Number NA
Dangerous Goods Class NA	Package Group NA

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.