

## AUBE00011 Berger Everlast Kitchen & Bathroom Low Sheen

### Introduction

Part A  
**668 LINE**

### Description and Image

Washable and stain resistant finish that is moisture resistant. Guaranteed to resist mould for 5 years if applied according to label directions. Low odour & low VOCs\* for fresher air.

### Features and Benefits

- Resists moisture and mould
- Highly washable
- Low VOC, Low Odour
- Keeps walls clean and fresh
- Most marks can be removed with a soft wet cloth
- Almost no paint smells

### Uses

Use Berger Kitchen and Bathroom Low Sheen on walls and ceilings. Particularly suited to wet areas such as kitchens, bathrooms or laundries.

✓ Wall ✓ Ceiling

### Precautions and Limitations

**All preparation and painting must conform to AS2311: The Painting of Buildings.**

Do not use at temperatures below 10C, or when the temperature of surface may fall below 10C during the drying period. Avoid exposure to steam and condensation for 48 hours after application. Although the film is dry to touch in 30 minutes allow 7 days for film to fully cure before washing.

**Tinted Colours:** Ensure that the paint is thoroughly shaken and stirred immediately after addition of tint to the can and again before use. Berger Kitchen and Bathroom is not a long term solution for poor building design and construction such as rising damp and inadequate ventilation.

### Performance Guide

Weather

**Designed for interior use only. Not recommended for exterior use.**

Heat Resistance

**Softens and sticks to other painted surfaces over 70C**

Water






**Suitable for use in wet areas**

Solvent

**Sensitive to aromatic hydrocarbons and alcohols**

Abrasion

**Good wet and dry burnish resistance and stain removal**

Typical Properties			
Gloss Level <b>Low Sheen</b>		Thinner <b>Water</b>	
Colour <b>Machine tinted to a wide range of colours from white, tint and extra tint.</b>			
Components <b>1</b>		Number of Coats <b>2*</b>	
Toxicity <b>Lead free. Dry film is non-toxic.</b>		V.O.C. Level <b>&lt; 5 g/L after tinting with Dulux Low VOC tint</b>	
Meets GBCA V.O.C. Requirements? <b>Yes</b> Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.			
Touch Dry <b>30 Minutes</b>			
Clean Up  <b>Water</b>			
Clean Up Description Clean all equipment with water			
Application Methods  <b>Air Spray</b>  <b>Airless Spray</b>  <b>Brush</b>  <b>Roller</b>			
Application Conditions	Solids by Volume		
	<input type="text" value="36"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="62"/>	<input type="text" value="62"/>	<input type="text" value="62"/>
Dry Film Per Coat (microns)	<input type="text" value="24"/>	<input type="text" value="24"/>	<input type="text" value="24"/>
Recoat Time (min/hours)	<input type="text" value="2 Hours"/>	<input type="text" value="Indefinite"/>	<input type="text"/>
Theoretical Spread Rate (m²/L)	<input type="text" value="16.1"/>	<input type="text" value="16.1"/>	<input type="text" value="16.1"/>

## Application Guide

### Surface Preparation

Remove all loose, powdery and flaking paint. Wash down with accent sugar soap and rinse with clean water to remove any dirt, oil or grease. Treat any mould present on the surface with a bleach solution diluted 3 to 1 with water. Wear Gloves and goggles. As above, use a scouring pad wet with bleach solution to lightly abrade the surface and ensure physical removal of stubborn areas of mould growth. Leave solution on the surface for 15 min then remove by washing down. Sand glossy surfaces. Fill any cracks or holes with a suitable accent filler, sand and dust off. Bare plasterboard or timber should be prepared by applying a suitable accent undercoat or primer.

### Application Procedure and Equipment

#### Brush, roller and spray

\* Some colours may require more than the recommended number of coats to achieve full opacity.

Stir well before use with a wide (approx 25mm) flat stirrer in a circular, lifting motion. Apply two coats by brush, roller or spray allowing at least two hours drying time between coats.

## Health and Safety

### Using Safety Precautions

Keep out of reach of children. Provide adequate ventilation. Keep windows and doors open during use and while drying. If spraying follow equipment guidelines and wear a suitable respirator.

**Please refer to SDS Link. In case of emergency, please call 1800 220 770.**

## Transport and Storage

### Pack A

#### 668 LINE

Size:

Weight:

1 Litre 4 Litre 10 Litres 15 Litre

1.5 Kg 5.8 Kg 14.5 Kg 22.0 Kg

Flash Point

NA

UN Number

NA

Dangerous Goods Class

NA

Package Group

NA

## Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from [www.duspecplus.com.au](http://www.duspecplus.com.au). Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.