

AUBG00008 Berger Gold Label Acrylic Satin

Introduction

Part A
676-82355

Approvals
APAS 0260/2

Description and Image

Berger Gold Label® Acrylic Satin Interior/Exterior is a high quality, washable, 100% acrylic finish which is ideal for both interior and exterior surfaces where a satin finish is desired.

Features and Benefits

- Water based
- Good opacity
- 100% Acrylic
- Excellent adhesion & flexibility
- Same day recoat, easy clean up and low odour.
- Saves application time, as two coat hiding allows quick application.
- For all areas requiring a hard wearing finish.
- Ideal for interior 'wet areas', and exterior substrates.

Uses

Use Berger Gold Label Acrylic Satin Interior/Exterior as a long lasting Satin finish on plaster, masonry, brick, concrete, render, fibro cement, and all suitably primed timber and metals. It's hard wearing acrylic formulation makes it perfect for areas subject to steam and moisture.






✓ Interior ✓ Exterior

Precautions and Limitations

All preparation and painting must conform to AS2311: The Painting of Buildings

Do not apply to roofs or surfaces used for the collection of drinking water. Do not paint at temperatures below 10C or when the temperature may fall below 10C during the drying period. Occasionally when dew or condensation forms on the newly dried film, a slight milky deposit will be observed on the film. This is quite normal and does not result in reduced performance. Simply hose or wipe off with a damp sponge and it will not reappear. Seven days are required after application to develop maximum hardness and stain removal properties. Most stains can be removed with gentle wiping.

Performance Guide	
Weather Good resistance to weathering, with very low level of chalking, colour change & dirt pick-up	Salt NA
Heat Resistance Resists up to 70C.	Water Suitable for use in wet areas, resists prolonged rain and condensation.
Solvent Sensitive to aromatic hydrocarbons, alcohols, esters, ketones & other strong solvents	Abrasion Good abrasion resistance.
Acid NA	Alkali NA

Typical Properties					
Gloss Level 20-30 at 60 degrees.	Thinner Water				
Colour Can be tinted to broad range of pastel colours.					
Components 1					
Toxicity Lead free. Dry film is non-toxic and conforms to AS1647, Part 3.	V.O.C. Level < 60g/L untinted				
Touch Dry 20 Minutes					
Clean Up  Water					
Clean Up Description Clean all equipment with water.					
Application Methods  Air Spray  Airless Spray  Brush  Roller					
Application Conditions	Solids by Volume				
	<input type="text" value="37"/>				
	Min				
Wet Film Per Coat (microns)	<input type="text" value="63"/>	Max	<input type="text" value="63"/>	Recommended	<input type="text" value="63"/>
Dry Film Per Coat (microns)	<input type="text" value="23"/>	<input type="text" value="23"/>	<input type="text" value="23"/>	<input type="text" value="23"/>	<input type="text" value="23"/>
Recoat Time (min/hours)	<input type="text" value="2 Hours"/>	<input type="text" value="Indefinite"/>	<input type="text" value=""/>	<input type="text" value=""/>	<input type="text" value=""/>
Theoretical Spread Rate (m ² /L)	<input type="text" value="16.1"/>	<input type="text" value="16.1"/>	<input type="text" value="16.1"/>	<input type="text" value="16.1"/>	<input type="text" value="16.1"/>

Application Guide

Surface Preparation

All surfaces must be thoroughly cleaned and free of all dirt, dust, grease, loose or flaking paint. Efflorescence or mould on masonry or concrete surfaces must be treated before painting. New concrete, mortar and cement render must be allowed to cure for 4 to 8 weeks depending on concrete thickness and drying conditions. Fill holes in masonry with grouting cement. Wash down with water with a stiff brush to remove all loose material. Flatten gloss paint by thorough sanding and wipe clean with a damp cloth, then apply preparation coats where necessary.

Application Procedure and Equipment

Brush, roller, conventional or airless spray

Stir contents thoroughly before and during use with a broad flat stirrer, using an upward lifting action.

Brush/Roller

Rinse brush or roller in water before starting and use while still slightly damp. Apply two full even coats direct from the container. Under hot or windy conditions or on very absorbent surfaces, up to 100 ml of clean water may be added per litre to assist application. Avoid excessive brushing or rolling back into paint which has been drying some minutes.

Airless/Conventional spray

Suitable for application by all standard spray equipment. If necessary thin with up to 100 ml of water per litre to aid atomisation.

Health and Safety

SDS Number
36306, 0

SDS Link
[View SDS Link](#)

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage

Pack A
676-82355

Size:

Weight:

4 Litre 10 Litre 15 Litre

5.3 Kg 13.2 Kg 20.0 Kg

Flash Point
NA

UN Number
NA

Dangerous Goods Class
NA

Package Group
NA

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.