

AUCA00019 Cabot's CFP Floor Oil Based Gloss

Introduction

Part A
864 82011

Description and Image

Cabot's CFP Floor Oil Based is a highly durable hard wearing finish specifically formulated for timber, parquetry, cork and MDF flooring. It is suitable for areas which are subject to scuffing and high traffic use. CFP Floor Oil Based will enhance the natural grain and colour of all timber flooring. For accelerated hardness and wear resistance, add Cabot's CFP Hardener to CFP Floor Oil Based.



Features and Benefits

- High durability.
- Resists stains & scratches.
- Enhances timber grain.
- Oil enriched.
- Highly durable polyurethane coating to protect timber floors for longer.
- CFP Floor is a tough coating suitable for areas subject to scuffing and high traffic use.
- Enhances the natural colour of the timber grain.
- Enriched with oil to nourish and protect the timber.

Uses

Timber, parquetry, cork and MDF flooring.

Precautions and Limitations

Do not apply this product if the temperature is below 10°C or above 35°C.

Performance Guide

Weather Interior only.	Heat Resistance Up to 100C
Water Good.	Abrasion Excellent resistance to wear.

Typical Properties

Gloss Level Gloss																	
Colour Clear																	
Components 1	Number of Coats 3																
Toxicity Lead free	V.O.C. Level < 480g/L																
Touch Dry 3 hours																	
Clean Up Description Mineral turpentine. To avoid spontaneous combustion of contaminated application cloths, soak application cloths in water or immediately spread used application cloths flat in a cool, well ventilated area to dry completely before disposal. Do not scrunch up or place cloths on top of each other.																	
Application Methods  Brush  Roller  Pad																	
Application Conditions	<table border="1"><tr><td>Solids by Volume 42</td></tr><tr><td>Min</td><td>Max</td><td>Recommended</td></tr><tr><td>Wet Film Per Coat (microns)</td><td></td><td>65</td></tr><tr><td>Dry Film Per Coat (microns)</td><td></td><td>27</td></tr><tr><td>Recoat Time (min/hours)</td><td>12 hours</td><td></td></tr><tr><td>Theoretical Spread Rate (m²/L)</td><td></td><td>16</td></tr></table>	Solids by Volume 42	Min	Max	Recommended	Wet Film Per Coat (microns)		65	Dry Film Per Coat (microns)		27	Recoat Time (min/hours)	12 hours		Theoretical Spread Rate (m ² /L)		16
Solids by Volume 42																	
Min	Max	Recommended															
Wet Film Per Coat (microns)		65															
Dry Film Per Coat (microns)		27															
Recoat Time (min/hours)	12 hours																
Theoretical Spread Rate (m ² /L)		16															
Typical Property Notes Spreading rate Approximately 16 square metres per litre depending on the porosity and condition of the timber.																	
Drying and re-coat time All timings quoted at 25C and 50% humidity. Cooler or humid conditions may require longer.																	

Application Guide

Surface Preparation

Note fill nail holes, cracks and other defects with Cabot's Wood Tone Putty after applying the first coat of this product for accurate colour matching. Remove stains, dirt, wax, grease and oil with mineral turpentine. Remove any polish with a suitable floor polish remover.

Bare timber

Sand the surface smooth using 180 - 240 grit sandpaper. Sand only in the direction of the grain. Remove all traces of sanding dust.

Previously coated floors

Thoroughly clean the surface with Cabot's Floor Clean and allow to dry. Sand with 180 - 240 grit sandpaper and remove all traces of sanding dust. Apply one coat to a small test area. Allow to dry for 12 hours. Press sticky tape firmly to the surface and pull off quickly. If the coating comes off, sand back to bare timber. If coating adheres well, sand the entire area with 180 - 240 grit paper for good adhesion, remove dust, then follow application instructions.

Application Procedure and Equipment

Note do not shake can. Stir thoroughly with a broad flat paddle before and during use. Apply product with a pad applicator, good quality brush or 6 - 10mm nap roller.

Bare timber floors

Use a brush to cut in around the edge of one section at a time. Apply along the length of 3 - 4 boards, keeping a wet edge to prevent lap marks. Allow to dry for a minimum of 12 hours, then lightly sand using 240 grit paper. Remove all sanding dust. If product does not sand to a fine powder it is not dry enough to re-coat. Apply the 2nd & 3rd coats as above.

Previously coated floors

Apply 2 coats working along the length of the boards. Sand between coats with 240 grit paper.

Staining bare timber floors

If staining is required, apply Cabot's Stain & Varnish Oil Based with a 6 - 10mm nap roller first, then coat with Cabot's CFP Floor following application instructions above.

Note to stain a previously coated timber floor, sand back to bare timber before staining.

Maintenance

Cabot's Floor Clean is recommended for regular cleaning. Maintain the sheen and appearance of the floor using Cabot's Floor Polish. This will prolong the life of the floor coating.

Walk on light traffic after 24 hours. Normal traffic after 72 hours.

Health and Safety

SDS Number 13661261	SDS Link View SDS Link
-------------------------------	---

Using Safety Precautions

Risk

Flammable. Irritating to skin. Avoid contact with skin and eyes. Provide adequate ventilation. If using indoors keep windows and doors open during use and while drying. If painting large areas, wear an organic vapour respirator. This paint is flammable, so eliminate any sources of ignition. Do not smoke.

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage

Pack A

864 82011

Size:

Weight:

10L 4L 1L

10.0Kg 4.0Kg 1.1Kg

Please refer to the Safety Data Sheet for full safety, health and transportation information.

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.