AUCA00017 Cabot's CFP Floor Water Based Gloss

Introduction

Part A
573 W0034

Description and Image

Cabot's CFP Floor Water Based is a fast drying, highly durable hard wearing finish specifically formulated for timber, parquetry, cork and MDF flooring and timber floating floors. It is suitable for areas which are subject to scuffing and high traffic use. CFP Floor Water Based makes refreshing your previously coated timber easier than ever as it eliminates the need to sand prior to coating. As it is water based, it has virtually no odour for a more comfortable working environment and clean up is easy with water.

Features and Benefits

- * No sanding required.
- High durability.
- Resists stains & scratches.
- Fast recoat - 3 hours.
- Low odour & non yellowing.
- * No sanding is required for pre-coated timber floors.
- Highly durable coating to protect timber floors for longer.
- CFP Floor Water Based is a tough coating suitable for areas subject to scuffing and high traffic use.
- Recoat after only 3 hours.
- Virtually no odour for a more comfortable working environment. Will not yellow.

Uses

Timber, parquetry, cork, MDF flooring and timber.

Precautions and Limitations

No sanding required
No sanding is required for pre-coated timber floors, preparation steps above must be followed. Please note new timber must be sanded. Do not apply this product if the temperature is below 10°C or above 35°C.

Performance Guide

Weather **Interior only.**	Heat Resistance **Up to 100C.**
Water **Good.**	Abrasion **Excellent resistance to wear.**

Typical Properties

Gloss Level
Gloss

Colour
Clear

Components	Number of Coats
1	**3**

V.O.C. Level
< 70g/L

Meets GBCA V.O.C. Requirements?
Yes

Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.

Touch Dry
30 minutes

Clean Up
Water

Application Methods
Brush **Roller** **Pad**

Application Conditions

Solids by Volume: **25**

	Min	Max	Recommended
Wet Film Per Coat (microns)			**64**
Dry Film Per Coat (microns)			**16**
Recoat Time (min/hours)	**3 hours**		
Theoretical Spread Rate (m²/L)			**16**

Typical Property Notes

Spreading rate
Approximately 16 square metres per litre depending on the porosity and condition of the timber.

Drying and re-coat time
All timings quoted at 25C and 50% humidity. Cooler or humid conditions may require longer.

Application Guide

Surface Preparation

No sanding required
No sanding is required for pre-coated timber floors, preparation steps below must be followed. Please note new timber must be sanded.
Note fill nail holes, cracks and other defects with Cabot's Wood Tone Putty after applying the first coat of this product for accurate colour matching.
Remove stains, dirt, wax, grease and oil with mineral turpentine. Remove any polish with a suitable floor polish remover.
Note floors with highly visible scratches, imperfections or floors that are severely worn must be sanded prior to coating.

Bare timber
Sand the surface smooth using 180 - 240 grit sandpaper. Sand only in the direction of the grain. Remove all traces of sanding dust.

Previously coated floors & timber floating floors
Thoroughly clean the surface with Cabot's Floor Clean and allow to dry. Apply one coat to a small test area. Allow to dry for 3 hours. Press sticky tape firmly to the surface and pull off quickly. If the coating comes off, sand back further to a sound surface.

Application Procedure and Equipment

Note do not shake can. Stir thoroughly with a broad flat paddle before and during use. Apply product with a pad applicator, good quality brush or 6 - 10mm nap roller.

Bare timber floors
Use a brush to cut in around the edge of one section at a time. Apply along the length of 3 - 4 boards, keeping a wet edge to prevent lap marks. Allow to dry for a minimum of 3 hours. For best results, lightly sand to remove any grain raise using 240 grit paper. Remove all sanding dust. Apply the 2nd & 3rd coats as above.

Previously coated floors
Apply 2 coats of CFP Floor Water Based working along the length of the boards. Allow 3 hours between coats.

Staining bare timber floors
If staining is required, apply Cabot's Stain & Varnish Water Based with a 6 - 10mm nap roller first, then coat with Cabots CFP Floor Water Based following application instructions above.
Note to stain a previously coated timber floor, sand back to bare timber before staining.

Maintenance
Cabot's Floor Clean is recommended for regular cleaning. Maintain the sheen and appearance of the floor using Cabot's Floor Polish. This will prolong the life of the floor coating.

Walk on
Light traffic after 16 hours. Normal traffic after 72 hours.

Health and Safety

SDS Number	SDS Link
22551	**View SDS Link**

Using Safety Precautions
Provide adequate ventilation. If using indoors keep windows and doors open during use and while drying.

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage

Pack A
573 W0034

Size:	Weight:
10L 4L 1L	**11.1Kg 4.5Kg 1.2Kg**

Please refer to the Safety Data Sheet for full safety, health and transportation information.

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.