

## AUAC00125 Dulux Acratex Venetian Plaster Modello

### Introduction

Line Shade  
**194X2050-24KG**  
**194X2055-24KG**

Variant  
**Venetian Plaster Modello White**  
**Venetian Plaster Modello Concrete**

### Description and Image

Venetian Plaster Modello is a traditional Interior Venetian coarse-grain plaster from yesteryear. It has a classic natural mineral look yielding a subdued satiny multi coloured marble effect

Venetian Plaster Modello is the perfect choice to decorate high-hand interiors and is widely used in foyers, hotel reception areas and concert halls.

It is an eco-friendly product, obtained from selected marble powders and genuine slaked lime baked in wood-fire kilns and aged for 8-10 months.



### Standards And Certifications



NATA Accredited:  
National Association of  
Testing Authorities



Quality  
ISO 9001

Certified System: Quality  
ISO 9001



Environment  
ISO 14001

Certified System:  
Environment ISO 14001

### Standards and Certifications

For details on these standards and certifications please reference the 'Approvals' section at the beginning of this document. Please contact your DuluxGroup representative for specific information on ESD credits / points.

### Uses

Venetian Plaster Modello is particularly suited to the preservative restoration of old historical buildings such as churches, palaces or villas interior's; to create surfaces of elevated aesthetic value in all settings whether modern or classic: halls, stairways, bathrooms, living rooms; to add a touch of elegance to the most refined public places such as hotels, restaurants, shops, etc.

Venetian Plaster Modello can also be used to create a number of specialist translucent marble effects.

## Typical Specifications

### Typical System

Title:

**AUAC02681 Dulux Venetian Plaster Modello / Bauta / Ombra on New Plasterboard [Interior]**

Preparation Guide

Refer Full Du Spec specification Sheet

AUAC02681 Dulux Acratex Venetian Plaster Modello / Bauta / Ombra on New Plasterboard [Interior]

Image Modello Cracked Stone pattern with 1st coat of Bauta Silver and 2nd coat Ombra (tinted black)




Coat	Product	Spread Rate (m <sup>2</sup> /L):	WFT (micron):	DFT (micron)
<b>1st Coat</b>	<b>VENETIAN PLASTER QUARTZ PRIMER</b>	<b>8</b>	<b>127</b>	<b>54</b>
<b>2nd Coat</b>	<b>VENETIAN PLASTER MODELLO</b>	<b>2.045</b>	<b>4.90</b>	<b>350</b>
<b>3rd Coat</b>	<b>VENETIAN PLASTER BAUTA</b>	<b>11</b>	<b>100</b>	<b>93.5</b>
<b>Optional</b>	<b>Venetian Plaster Ombra</b>	<b>11</b>	<b>100</b>	<b>93.5</b>
Minimum System DFT: <b>591</b>				

Notes:

Venetian Plaster Modello can be finished a number of Traditional and imaginative ways to produce a number of effects.  
E.g. Travertino a traditional vertical or horizontal scratch finish

## System Performance Testing Data

Test Result Name:	Test Method:	Unit of Measure:	Result:	Comments:
<b>Ignitability Index</b>	<b>AS1530.3</b>	<b>0-20</b>	<b>0</b>	<b>AWTA Test Number 20-001596</b>
<b>Spread of Flame Index</b>	<b>AS1530.3</b>	<b>0-10</b>	<b>0</b>	<b>AWTA Test Number 20-001596</b>
<b>Heat Evolved Index</b>	<b>AS1530.3</b>	<b>0-10</b>	<b>0</b>	<b>AWTA Test Number 20-001596</b>
<b>Smoke Developed Index</b>	<b>AS1530.3</b>	<b>0-10</b>	<b>2</b>	<b>AWTA Test Number 20-001596</b>

Typical Properties			
V.O.C. Content <b>0.1</b>			
Clean Up water			
Sizes <b>24kg</b>			
Meets GBCA V.O.C. Requirements? <b>Yes</b> Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinters required for non-factory packaged colours.			
Application Methods  <b>Trowel</b>			
Specifications	Solids by Volume		
	<b>71.36</b>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<b>380</b>	<b>490</b>	<b>380</b>
Dry Film Per Coat (microns)	<b>271</b>	<b>350</b>	<b>271</b>
Theoretical Spread Rate (m <sup>2</sup> /L)	<b>2.632</b>	<b>2.045</b>	<b>2.632</b>
Drying Time			
	Min	Max	Recommended
Recoat Time (min/hours)	<b>16-24 hrs</b>		
Typical Property Notes Note; 2.632 m <sup>2</sup> /L equates to 0.7 kg/m <sup>2</sup> per coat OR approx 34.3m <sup>2</sup> per pail 2.045 m <sup>2</sup> /L equates to 0.9 kg/m <sup>2</sup> per coat OR approx 21.6m <sup>2</sup> per pail Lower spread rates for deeper patterned finishes			

## Application Guide

### Surface Preparation

#### Interior:

**Preparation:** on civil plaster or old mineral paints as long as they are not powdery, are in good condition and sufficiently rough, apply directly. On supports of the type: gesso, gypsum, plasterboard, old synthetic or powdery paints, stucco smoothing etc, apply a coat of primer to the point of saturation and subsequently a coat of Venetian Plaster Modello in advance with appropriate products the presence of stains of various types or any saline efflorescence. In the case of irregular supports, whether interior or exterior, with uneven absorption rates, restored plaster, stains, etc., the application of a layer of Intocalce with a steel trowel is recommended in order to even out the surface and create the ideal base for even absorption.

### Application Procedure and Equipment

Apply one layer of Venetian Plaster Modello with a steel trowel or spatula, then pattern as required when the surface has dried slightly, making sure that it is neither completely dry and nor excessively wet, proceed to the polishing by going over the surface repeatedly with a spatula, pressing hard.

## Health and Safety

SDS Number  
**DLX003584**

SDS Link  
[View SDS Link](#)

### Using Safety Precautions

#### Safety Directions:

Causes skin irritation.  
Causes serious eye damage.  
Keep out of reach of children.  
Read the label before opening or using.  
Avoid breathing vapour.  
Wear protective clothing, gloves, eye/face protection and suitable respirator/dust mask as required.  
Wash contaminated clothing before re-use.  
Wash hands, face and all exposed skin thoroughly after handling.  
Store in a well-ventilated place and away from oxidising agents, acids and foodstuffs.  
Do not empty into drains.

**Please refer to SDS Link. In case of emergency, please call 1800 220 770.**

### Precautions and Limitations

**This product data sheets shall be read in conjunction with the Dulux specification.**

To ensure colour uniformity and for optimum performance, Dulux recommend a full coating system including a Membrane topcoat.

For **all** systems, the Texture &/or Base Coat should be tinted in accordance with Tint Guide to the specified topcoat colour (or a colour as close as possible to the specified colour as product and Acratex tint rules allow).

**Important:** Not all colours are suitable for exterior use.

Ensure that you have adequate tinted stock to complete the job in one application.

All material must be thoroughly cross-mix to ensure tint uniformity.

It is recommended to hold a volume of finish material for future maintenance touch-ups

Practical spreading rates will vary from quoted theoretical figures depending on substrate porosity, surface roughness, overspray losses, application methods and environmental conditions (e.g. wind).

- Do not apply paint if Relative Humidity is above 85% or temperature is within 3°C of Dew Point.
- Do not apply if the surface temperature is greater than 40°C or below 10°C, or likely to fall below 10°C during the application or drying period.
- Dry times apply to a single coat at recommended spread rate and at 25°C and 50% Relative Humidity
- Allow longer times under cool, moist, or still conditions and or when applied at high film builds.
- Protect from dew, rain and frost for 48 hours when apply at the recommended spread rate.
- Avoid application in hot, windy conditions or on hot surfaces cool the surface by hosing with water and paint the cool damp surface.
- The exterior texture coatings should be cleaned on a regular basis.
- This will help maintain your overall aesthetic appearance and preserve your Acratex Texture coating system.

Cleaning once every year will remove light soil as well as grime and airborne pollutants refer Dulux Acratex Care & Maintenance Guide.

### Transport and Storage

Line Shade /Pack A

**194X2050-24kg**

Size:

Weight:

**24kg**

**24kg**

### Further Information

**Venetian Plaster Web Page**

### Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from [www.duspecplus.com.au](http://www.duspecplus.com.au). Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.