

**AUBE00036 Berger Premium Triple Prep Oil Base Undercoat**

**Introduction**

Part A  
**830-70021**

**Description and Image**

**Berger Premium Triple Prep Oil Base** is an oil based interior/exterior undercoat with excellent filling and sanding properties and good hold-out for gloss and semi gloss enamels.

**Features and Benefits**

- General purpose
- Good filling & sanding
- Good enamel hold out
- Can be used on a wide range of interior and exterior surfaces.
- Both application and sanding down are quick and easy.
- Gloss finishes are sharp and satins an even sheen.

**Uses**

Use Berger Premium Triple Prep as a general purpose undercoat over bare interior timber and suitably primed exterior timber and metal, and suitably sealed masonry, hardboard, etc.




✓ Interior ✓ Exterior

**Precautions and Limitations**

**All preparation and painting must conform to AS2311: The Painting of Buildings.**  
Do not apply if the surface temperature is below 10C or conditions indicate it will fall below 10C during the drying period.  
Do not apply externally when weather is doubtful, or late in afternoon during winter, as frost, rain or dew on the uncured undercoat may result in loss of film integrity and impair durability of the system.

**Performance Guide**

Weather <b>Excellent when topcoated.</b>	
Heat Resistance <b>Up to 120C. Premature yellowing &amp; embrittlement will occur if film is subject to continuous heat.</b>	Water <b>Excellent when topcoated.</b>
Solvent <b>Resists alcohols and hydrocarbons. Film is vulnerable to attack from other strong solvents.</b>	

Typical Properties			
Gloss Level <b>NA</b>	Thinner <b>Mineral Turpentine</b>		
Colour <b>White</b>			
Components <b>1</b>			
Toxicity <b>Lead free. Dry film is non-toxic.</b>	V.O.C. Level <b>&lt; 365g/L untinted</b>		
Sanding Properties <b>Very good</b>			
Touch Dry <b>6 Hours</b>			
Clean Up  <b>Thinner</b>			
Clean Up Description Clean all equipment with mineral turpentine.			
Application Methods  <b>Air Spray</b>  <b>Airless Spray</b>  <b>Brush</b>  <b>Roller</b>			
Application Conditions	Solids by Volume		
	<input type="text" value="53.6"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="75"/>	<input type="text" value="75"/>	<input type="text" value="75"/>
Dry Film Per Coat (microns)	<input type="text" value="40"/>	<input type="text" value="40"/>	<input type="text" value="40"/>
Recoat Time (min/hours)	<input type="text" value="24 Hours"/>	<input type="text" value="Indefinite"/>	<input type="text"/>
Theoretical Spread Rate (m <sup>2</sup> /L)	<input type="text" value="13.3"/>	<input type="text" value="13.3"/>	<input type="text" value="13.3"/>

Application Guide
<p>Surface Preparation</p> <p>All surfaces must be thoroughly dry, clean and free of all loose dirt, grease, mould, mildew and wax, surface chalk and loose or flaking paint. Sand smooth, dust down, fill and prime in accordance with the requirements of the chosen system.</p>
<p>Application Procedure and Equipment</p> <p>Brush, roller, conventional or airless spray. Stir contents thoroughly before and during use.</p> <p><b>Brush/Roller:</b> Apply by brush or roller, full even coats direct from the container. If necessary up to 50ml per litre of mineral turpentine may be added to ease application.</p> <p><b>Airless/Conventional Spray:</b> Suitable for application by all standard spray equipment. If necessary thin with up to 100ml per litre of mineral turpentine to aid atomisation.</p>

Health and Safety	
<p>SDS Number <b>13683350, 0</b></p>	<p>SDS Link <a href="#">View SDS Link</a></p>
<p><b>Please refer to SDS Link. In case of emergency, please call 1800 220 770.</b></p>	

Transport and Storage	
<p>Pack A <b>830-70021</b></p>	
<p>Size: <b>500mL, 1L, 4L, 10L</b></p>	<p>Weight: <b>800g, 1.6Kg, 6.4Kg, 15.8Kg</b></p>
<p>Flash Point <b>&gt;23C</b></p>	<p>UN Number <b>1263</b></p>
<p>Dangerous Goods Class <b>3</b></p>	<p>Package Group <b>III</b></p>

**Disclaimer**

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from [www.duspecplus.com.au](http://www.duspecplus.com.au). Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.