

## AUAC00044 Dulux Acratex AcraSkin

### Introduction

Line Shade  
**19485675-15L AcraSkin Pastel Base**

Product Line  
**19485676-15L AcraSkin Ultra Deep toned Base**

Line Shade  
**19485677-15L AcraSkin Extra Bright Toned Base**

Approval  
**AS4548.1, AS4548.2 : Long Life Coatings for Masonry**

### Description and Image




**Dulux Acratex AcraSkin** is a high performance weather proofing, highly flexible, Elastomeric Membrane coating that can be applied by conventional nap roller or low profile texture roller. Conforms to Australian Standard AS4548 Long Life Coatings for Masonry, Category 1 and 2



### Features and Benefits

- High Solids - High Film Build
- Flexibility
- Crackbridging
- Water Resistance
- Vapour Permeability (Breathability)
- Guaranteed long term exterior durability.
- 300%
- 9 times Dry Film Thickness
- Extremely low water transmission
- 54.8 g / 24 hr / sqm (Resistance to blistering)

**Standards And Certifications**

 <p>NATA Accredited: National Association of Testing Authorities</p>	 <p>Certified System: Quality ISO 9001</p>	 <p>Certified System: Environment ISO 14001</p>	
---	---	--	--

**Standards and Certifications**

For details on these standards and certifications please reference the 'Approvals' section at the beginning of this document. Please contact your DuluxGroup representative for specific information on ESD credits / points.

**Uses**

Dulux Acratex AcraSkin has been developed for use as a Masonry Protective Coating, providing weatherproofing and optimum crack bridging performance. It provides a finish with excellent water resistance & barrier properties against moisture ingress, carbonation and surface cracking, at the same time significantly improving the buildings aesthetics.

Dulux Acratex AcraSkin is ideal where a mid build, Elastomeric system is required with ultimate flexibility and resistance to water ingress.

Dulux Acratex AcraSkin is suitable for use as a stand-alone protective Membrane system (suitably primed), or as a performance Shield-Membrane over Dulux Acratex Texture Coatings to elevate total system performance.

**Typical Specifications**

Typical System

Title:

**Typical System for site mixed or Pre Bagged Cement Renders where maximum Crack bridging is required**

Preparation Guide

Refer Specification for full details.

AUAC00859 Dulux Acratex AcraSkin Low Gloss / Green Render Sealer / on New Cement Render [Exterior]

At Commencement of coating system application to the substrate it shall be deemed that the Applicator has certified that the surface which it is to be applied to is fit receive the specified coating(s) system. When the Applicator is preparing the site sample for approval he should advise the Project Superintendent if the substrate condition is not of sufficient standard to produce the specified finish.

The substrates surface condition must be of consistent density/integrity and not subject to continual wetting, hydrostatic pressure, spalling or other conditions that will cause premature coating failure

Coat	Product	Spread Rate (m <sup>2</sup> /L):	WFT (micron):	DFT (micron)
<b>1st Coat</b>	<b>Green Render Sealer</b>	<b>8</b>	<b>47</b>	<b>20</b>
<b>2nd Coat</b>	<b>968 AcraSkin</b>	<b>4</b>	<b>244</b>	<b>125</b>
<b>3rd Coat</b>	<b>968 AcraSkin</b>	<b>4</b>	<b>244</b>	<b>125</b>
				Minimum System DFT: <b>270</b>

Notes:





Refer Specification for full details.

AUAC00859 Dulux Acratex AcraSkin Low Gloss / Green Render Sealer / on New Cement Render [Exterior]

A Dulux warranty will be provided confirming protection against flaking & peeling for a period of Fifteen years when this full Acratex system is applied by a Dulux Acratex trained applicator, according to specification, & at the specified spreading rates, & to the surface preparation details described in the Dulux Acratex Specification Manual.

System Performance Testing Data				
Test Result Name: <b>Carbon Dioxide Diffusion Resistance</b>	Test Method: <b>AS 4548.5 Appendix D</b>	Unit of Measure: <b>cm2 per sec</b>	Result: <b>2.5 x 10 -07</b>	Comments: <b>Independent Test Results Diffusion resistance coefficient (u) = 666200 Equivalent thickness of Concrete (Sc) = 83cm Equivalent air layer thickness (R) = 333m</b>
<b>Chloride Ion Diffusion Resistance</b>	<b>AS 4548.5 Appendix E</b>	<b>cm2 per sec</b>	<b>0.8 x 10 -12</b>	<b>Independent Test Results</b>
<b>Water Vapour Transmission</b>	<b>AS 4548.5 Appendix C</b>	<b>g/m2/24hr</b>	<b>54.8</b>	<b>Independent Test Results Vapour Diffusion coefficient of film = 1.6x10-04cm2sec Vapour resistance coefficient (u) = 1550 Permeance of film = 4.3x10-07g/Pasm2 Equivalent air layer thickness (Sd) = 1m</b>
<b>Water Transmission Resistance</b>	<b>AS 4548.5 Appendix C</b>	<b>g/m2/24hr/kPa</b>	<b>&lt;1</b>	<b>Independent Test Results</b>
<b>Crack Bridging Ability "B"</b>	<b>AS 4548.5 Appendix F</b>	<b>x Film Build</b>	<b>9.3</b>	<b>Independent Test Results Static Test Test Speed of 0.5mm/min Test Temp =23+/-3 degrees</b>
<b>Wind Driven Rain</b>	<b>ASTM D6904</b>	<b>Pass / Fail</b>	<b>Pass No Leaks</b>	<b>Independent Test Results  24h –exposure to continuous water spray (rain) and a dynamic pressure equivalent to a 98mph wind velocity</b>
<b>Tensile Strength</b>	<b>AS1145</b>	<b>MPa</b>	<b>1.58</b>	<b>Independent Test Results</b>
<b>Heat &amp; Smoke Release Rate</b>	<b>AS3837</b>	<b>m2/kg</b>	<b>29.9</b>	<b>Independent Test Results @ Irradiance level of 50-kW/m2 Group 1 Classification</b>
<b>Elongation</b>	<b>AS 4548.1</b>	<b>%</b>	<b>308</b>	<b>Independent Test Results Specimen type 2 Test speed 50mm/min</b>

Performance Guide	
Salt <b>Resists salt spray.</b>	Heat Resistance <b>Up to 90C (dry).</b>
Water <b>Watertight Film - extremely low water transmission</b>	Solvent <b>Resists alcohol and aliphatic hydrocarbons. Sensitive to other strong solvents.</b>
Abrasion <b>Good resistance to abrasion.</b>	Acid <b>Slightly softening with dilute acids.</b>
Alkali <b>New Cement / Concrete surfaces should be allowed to cure for 28 days to stabilise alkalinity</b>	

Typical Properties			
V.O.C. Content <b>&lt; 46 g/L untinted</b>			
Clean Up  <b>Water</b> Clean up water Clean all equipment with water.			
Application Methods  <b>Airless Spray</b>  <b>Brush</b>  <b>Roller</b>			
Specifications	Solids by Volume <input type="text" value="51.25"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="244"/>	<input type="text" value="488"/>	<input type="text" value="322"/>
Dry Film Per Coat (microns)	<input type="text" value="125"/>	<input type="text" value="250"/>	<input type="text" value="165"/>
Theoretical Spread Rate (m <sup>2</sup> /L)	<input type="text" value="4.1"/>	<input type="text" value="2.1"/>	<input type="text" value="3.1"/>
Drying Time	Min	Max	Recommended
Recoat Time (min/hours)	<input type="text" value="4 Hours"/>	<input type="text" value="Indefinite"/>	<input type="text"/>

Application Guide
<p>Surface Preparation</p> <p>All surfaces must be cured, clean, sound and free of all contaminants such as form oils, release agents and mortar splashes. Surface imperfections, misalignments and protrusions must be levelled and patched and completely flush to surrounding surfaces. Metal, tie wire, etc. on surface must be removed or treated against corrosion. Prime substrate with Dulux Acratex AcraPrime SB. Ensure that it is cured completely and covers the substrate evenly. Patch with Dulux Acratex AcraPatch after priming, and then prime using Dulux Acratex AcraPrime WB or Green Render Sealer.</p>
<p>Application Procedure and Equipment</p> <p><b>Brush, Roller, Medium Textured Roller, Airless Spray.</b> When cutting in edges, brush and roll-in a continuous process to avoid differences in gloss level. Application on single areas should be completed uninterrupted. All independent tests are available on request. Product should be thoroughly mixed before use. Refer to the Dulux Acratex Application Manual for detailed application instructions.</p> <p><b>Nap roller finish:</b> Apply 2 coats (minimum) using a 10 - 20mm Nap roller at 4 sq.m / litre</p> <p><b>Low profile texture (requires higher material consumption):</b> Apply 1 coat with a low profile black Texture Roller at 2-3 sq.m / litre Apply a 2nd (finishing coat) with a nap roller at 4 sq.m / litre</p>

Health and Safety	
SDS Number <b>DLX001296</b>	SDS Link <a href="#">View SDS Link</a>
Using Safety Precautions May cause an allergic skin reaction. When spraying, inhalation of mists may produce respiratory irritation. Wear eye protection and when spraying or sanding wear an appropriate respiratory mask	
<b>Please refer to SDS Link. In case of emergency, please call 1800 220 770.</b>	

Precautions and Limitations
<p><b>This product data sheets shall be read in conjunction with the Dulux specification.</b></p> <p>To ensure colour uniformity and for optimum performance, Dulux recommend a full coating system including a Membrane topcoat. For <b>all</b> systems, the Texture &amp;/or Base Coat should be tinted in accordance with Tint Guide to the specified topcoat colour (or a colour as close as possible to the specified colour as product and Acratex tint rules allow).</p> <p><b>Important:</b> Not all colours are suitable for exterior use.                      Ensure that you have adequate tinted stock to complete the job in one application.                      All material must be thoroughly cross-mix to ensure tint uniformity.                      It is recommended to hold a volume of finish material for future maintenance touch-ups</p> <p>Practical spreading rates will vary from quoted theoretical figures depending on substrate porosity, surface roughness, overspray losses, application methods and environmental conditions (e.g. wind).</p> <ul style="list-style-type: none"> <li>• Do not apply paint if Relative Humidity is above 85% or temperature is within 3°C of Dew Point.</li> <li>• Do not apply if the surface temperature is greater than 40°C or below 10°C, or likely to fall below 10°C during the application or drying period.</li> <li>• Dry times apply to a single coat at recommended spread rate and at 25°C and 50% Relative Humidity</li> <li>• Allow longer times under cool, moist, or still conditions and or when applied at high film builds.</li> <li>• Protect from dew, rain and frost for 48 hours when apply at the recommended spread rate.</li> <li>• Avoid application in hot, windy conditions or on hot surfaces cool the surface by hosing with water and paint the cool damp surface.</li> <li>• The exterior texture coatings should be cleaned on a regular basis.</li> <li>• This will help maintain your overall aesthetic appearance and preserve your Acratex Texture coating system.</li> </ul> <p>Cleaning once every year will remove light soil as well as grime and airborne pollutants refer Dulux Acratex Care &amp; Maintenance Guide.</p>

Transport and Storage	
Line Shade /Pack A <b>19485675-77</b>	Shipment Name <b>Not dangerous goods.; No special transport requirements.</b>
Size: <input type="text" value="15 Litre"/>	Weight: <input type="text" value="22 Kg"/>

Further Information
<b>ACRATEx CARE &amp; MAINTENANCE GUIDE</b>

#### Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from [www.duspecplus.com.au](http://www.duspecplus.com.au). Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.