

## AUDU00148 Dulux 1 Step Prep

### Introduction

Part A  
630D0131

#### Approvals

**APAS 0172 & Green Star: Complies with the requirements for the Indoor Environment Quality credit in Green Star Australia rating tools.**

### Description and Image

**Dulux 1 Step Prep is a multi-surface Primer Sealer Undercoat.**

Dulux 1 Step Prep is your first step toward a superior long lasting paint finish. With Mould resistance and stain blocking of tannin and flash rust\*, Dulux 1 Step Prep ensures your interior or exterior paint shines now and into the future. Use Dulux 1 Step Prep for all paintable surfaces around your home including interior and exterior walls, ceilings, doors, windows, trim, and especially where mould is a problem including kitchens, bathrooms & outside areas.


\*1Step prevents rusting when applied over small metal surfaces such as nails or bolt heads. over large steel surfaces, use Dulux all metal primer.




### Features and Benefits

- Superior adhesion
- Mouldshield technology
- Interior & exterior use
- No sanding required on most surfaces
- Mould resistance
- Excellent coverage

### Standards And Certifications



Australian Paint Approval Scheme



Can contribute towards satisfying Green Star Credits

#### Standards and Certifications

For details on these standards and certifications please reference the 'Approvals' section at the beginning of this document. Please contact your DuluxGroup representative for specific information on ESD credits / points.

**Uses**

Interior and exterior surfaces including paperfaced plasterboard, timber, MDF, brick, masonry, concrete, cement sheet, Zinalume, galvanised iron, PVC, and previously painted surfaces.

✓ Interior ✓ Exterior

**Precautions and Limitations**

**All preparation and painting must conform to AS2311: The Painting of Buildings.**

Do not overspread or exceed 14 sqm/L per coat. In hot weather, rinse brush every half hour or use two and keep one standing in water.

Do not apply if temperature is under 10C, or when temperature of surface may fall below 10C during the drying period, otherwise film formation will not be complete and poor properties will result.

\*Flash rust resistant means spot priming, with a metal primer, over nail heads, bolts and similar metal surfaces is not normally required. 1-Step Prep can be applied over any surface listed under "Uses" which may include nail heads and bolts. On large metal surfaces Precision All Metal Primer is recommended. Call Help & Advice, 132525, if further assistance is required.

Although 1-Step Prep is suitable for most timbers, tannin rich timbers may require 1-Step Oil based to prevent tannins from bleeding to the surface.

**Performance Guide**

Weather

**Excellent when used as part of approved system.**

Heat Resistance

**Up to 70C**

Water

**Excellent when topcoated with approved topcoat.**

Solvent

**Sensitive to aromatic hydrocarbons, alcohols and ketones.**

Abrasion

**Good when topcoated.**

Typical Properties			
Gloss Level <b>Low Sheen</b>	Thinner <b>Water</b>		
Colour <b>White, may be tinted up to 28mL (1Y) per litre.</b>			
Components <b>1</b>			
V.O.C. Level <b>&lt;31 g/L inclusive of Dulux Low VOC tinter</b>			
Meets GBCA V.O.C. Requirements? <b>Yes</b> Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.			
Sanding Properties <b>Excellent</b>			
Touch Dry <b>30 minutes</b>			
Clean Up <b>Water</b>			
Clean Up Description Clean all equipment with water			
Application Methods <b>Air Spray</b> <b>Airless Spray</b> <b>Brush</b> <b>Roller</b>			
Application Conditions	Solids by Volume		
	<input type="text" value="40"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="71"/>	<input type="text" value="71"/>	<input type="text" value="71"/>
Dry Film Per Coat (microns)	<input type="text" value="29"/>	<input type="text" value="29"/>	<input type="text" value="29"/>
Recoat Time (min/hours)	<input type="text" value="2 hours"/>	<input type="text" value="Indefinite"/>	<input type="text" value="2 hours"/>
Theoretical Spread Rate (m <sup>2</sup> /L)	<input type="text" value="14"/>	<input type="text" value="14"/>	<input type="text" value="14"/>

**Application Guide**

Surface Preparation

All surfaces must be thoroughly cleaned and free of all loose dirt, grease, stains, mould, surface chalk and loose or flaking paint. Wash unpainted timber surfaces with a suitable timber cleaner to remove excess tannins or greyed timber. New timber surfaces should also be sanded smooth and dusted down prior to priming. Fill nail holes, imperfections and cracks with a suitable filler, sand and dust off. For set plaster or plasterglass use sealer binder as the prepcoat.

Application Procedure and Equipment

Brush, roller, conventional or airless spray.

**Note:** Spray application is not recommended for priming timber surfaces.

Stir contents thoroughly before and during use. Apply direct from the can. May be applied to dampened surfaces. If applied over dry, porous surfaces, dampen surfaces before applying.

**Brush:** Wet brushes with water prior to use to avoid clogging. Apply a full even coat direct from the container. Under hot conditions it may be necessary to thin with up to 100mL/L of clean water.

**Roller:** Using a medium nap roller apply a full even coat and finish with light parallel strokes without reloading the roller.

**Airless/Conventional Spray:** Suitable for application by all standard spray equipment. If necessary thin with up to 100mL/L of water water to aid atomization.

**Note:** Spray application is not recommended for priming timber surfaces.

**Health and Safety**

SDS Number  
**DLXGHSEN002997**

SDS Link  
[View SDS Link](#)

**Please refer to SDS Link. In case of emergency, please call 1800 220 770.**

**Transport and Storage**

Pack A  
**630-D0131**

Size:

0.5L, 1L, 2L, 4L, 10L, 15L

Weight:

0.71kg, 1.42kg, 2.84kg, 5.68kg, 14.2

Flash Point  
**N/A**

UN Number  
**N/A**

Dangerous Goods Class  
**N/A**

Package Group  
**N/A**

#### Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from [www.duspecplus.com.au](http://www.duspecplus.com.au). Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.