

AUAV00071 Dulux Avista Polyaspartic Two Pack High Gloss / over Dulux Avista Resurfacing System on Previously Coated Concrete floors [Exterior]

Scope of Works

Avista Resurfacing Compound system for use over a concrete substrate.

Substrate and Substrate Preparation

Substrate Notes

Concrete is a mixture of Portland cement, fine and coarse mineral aggregates, water and admixtures. Concrete floor slab construction consists of concrete poured into formwork in which reinforcing steel had been laid. The formwork (usually timber) holds the slab together as the concrete cures. The concrete should be kept wet according to best practice methods to allow the cement to fully hydrate during the curing process of 4-6 weeks to allow it to reach its design strength. Methods include ponding, wet hessian, wet sand or plastic sheet. If allowed to dry out prematurely, concrete will develop laitance, a weak, friable layer on the surface.

A waterproofing membrane should be laid underneath the slab to prevent moisture from rising up from the soil through the slab and causing efflorescence. The presence of laitance or efflorescence will interfere with coating adhesion.

Substrate Preparation Notes

ASSESS SUITABILITY

Inspect to determine the degree of deterioration of existing coatings. Identification of the existing coating is also very helpful in determining the system procedure. Check coating adhesion using the cross-hatch test as per AS 1580.408.2 : Paints and related materials - Methods of test - Adhesion (cross-cut)

CLEAN SURFACE

Clean surface to remove all dirt, dust, grease, oil, efflorescence, laitance, powdery surfaces and all other surface contaminants by high pressure water cleaning.

REPAIR SURFACE IMPERFECTIONS








Grind out cracks and fill with AVS EPOXY CONCRETE CRACK REPAIR 1.5L-FC378187-1.5L
Feather off areas where previous resurfacing product has lifted. Do NOT fill expansion joints.

PRIME

Spot prime bare concrete areas with AVS RESURFACING PRIMER 10L-FD578046-10L. (Can be coated immediately with Resurfacing product).
Then trowel resurfacing product to uniform film build.

Coating System Summary

- | | |
|------------|---|
| • Primer | Dulux Avista Resurfacing Primer |
| • 1st Coat | Dulux Avista Resurfacing Base Compound |
| • 2nd Coat | Dulux Avista Resurfacing Base Compound |
| • 3rd Coat | Dulux Avista Polyaspartic Two Pack High Gloss |

Coating System			
Primer — Dulux Avista Resurfacing Primer			
Coat Type Primer	Datasheet AUAV00007 Dulux Avista Resurfacing Primer		
Read the full Datasheet details at Dulux Avista Resurfacing Primer			
Components 1			
Application Methods  Roller  Floor Squeegee  Broom			
Theoretical Spread Rate (m ² /L)	Min <input type="text"/>	Max <input type="text"/>	Recommended 10
Meets GBCA V.O.C. Requirements? Not Applicable			
<p>Coating Application Details</p> <p>Shake Avista Primer container well before opening and then dilute 1 part Primer to 3 parts water in a clean bucket (4 litres of mixed Primer will cover approximately 40m² depending on the porosity of the concrete).</p> <p>Apply the mixed primer to the surface using a soft broom, roller or sprayer. Spread evenly across the surface so primer doesn't pool as this can affect adhesion. Whilst the surface is still wet, the resurfacing coating can be applied.</p> <p>Whilst the surface is still wet, Dulux Avista Resurfacing Compound can be applied as per the instructions on the bag.</p>			
1st Coat — Dulux Avista Resurfacing Base Compound			
Coat Type 1st Coat	Datasheet AUAV00006 Dulux Avista Resurfacing Base Compound		
Read the full Datasheet details at Dulux Avista Resurfacing Base Compound			
Components 3			
Pot Life approx. 30 minutes, depending on ambient conditions	Yield 12.5L		
Application Methods  Floor Squeegee  Broom  Trowel  Hopper Gun			
Theoretical Spread Rate (m ² /L)	Min 15	Max 30	Recommended <input type="text"/>
Recoat Time **	40	NA	<input type="text"/>
V.O.C. Level 11 grams per litre	Meets GBCA V.O.C. Requirements? Not Applicable		
<p>Coating Application Details</p> <p>Add required amount of clean potable water (3.6 - 4.0 L) in a clean 20L bucket and add Avista Resurfacing Colour Oxide and mix thoroughly with mechanical mixer at low speed until mix colour is uniform.</p> <p>Slowly add Dulux Avista Resurfacing Base Compound, mixing continually.</p>			

Once full content has been added, mix for a further 3 minutes. This step is critical in activating the polymers to achieve an even consistent mixture.

First coat should always be applied to a damp, primed surfaces. Applicable to all trowel or squeegee application methods.

Squeegee/Trowel application (recommended for first coat)

Pour a manageable quantity of Dulux Avista mixture onto the damp, primed concrete surface. Use squeegee or trowel evenly spread the resurfacing compound over the surface.

Do not exceed a thickness of 4 mm per coat, as this may lead to shrinkage cracking.

Subsequent trowel or spray coats can be applied to achieve desired decorative finish.

Spray application

Application will require a moisture trap air compressor & hopper gun. Recommended minimum compressor specs: 12 cfm with a 70L tank. Add mix to hopper, ensuring not to overfill - recommend half full.

Before applying to surface, spray on separate fibro test board to obtain desired texture. Adjust pressure to vary texture.

Spray evenly across the surface, holding the hopper approximately 600mm from the ground.

Once area has been completely covered, allow to dry sufficiently to walk on.

Minimum 2 coats at total of minimum 3mm thickness required to achieve sufficient wear factor.

The Dulux Avista Resurfacing System must be sealed once the surface is completely dry. Options for sealing include:

- Dulux Avista General Purpose Sealer (S/G or matt)
- Dulux Avista Extended Wear Sealer
- Dulux Avista 2 Pack Urethane
- Dulux Avista Polyaspartic Sealer

SDS Number

SDS Link

[View SDS Link](#)

2nd Coat — Dulux Avista Resurfacing Base Compound

Coat Type
2nd Coat

Datasheet
AUAV00006 Dulux Avista Resurfacing Base Compound

Read the full Datasheet details at [Dulux Avista Resurfacing Base Compound](#)

Components
3

Pot Life
approx. 30 minutes, depending on ambient conditions

Yield
12.5L

Application Methods



Floor Squeegee



Broom



Trowel



Hopper Gun

	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)	15	30	
Recoat Time **	40	NA	

V.O.C. Level
11 grams per litre

Meets GBCA V.O.C. Requirements?
Not Applicable

Coating Application Details

Add required amount of clean potable water (3.6 - 4.0 L) in a clean 20L bucket and add Avista Resurfacing Colour Oxide and mix thoroughly with mechanical mixer at low speed until mix colour is uniform.

Slowly add Dulux Avista Resurfacing Base Compound, mixing continually.

Once full content has been added, mix for a further 3 minutes. This step is critical in activating the polymers to achieve an even consistent mixture.

First coat should always be applied to a damp, primed surfaces. Applicable to all trowel or squeegee application methods.

Squeegee/Trowel application (recommended for first coat)

Pour a manageable quantity of Dulux Avista mixture onto the damp, primed concrete surface. Use squeegee or trowel evenly spread the resurfacing compound over the surface.

Do not exceed a thickness of 4 mm per coat, as this may lead to shrinkage cracking. Subsequent trowel or spray coats can be applied to achieve desired decorative finish.

Spray application

Application will require a moisture trap air compressor & hopper gun. Recommended minimum compressor specs: 12 cfm with a 70L tank. Add mix to hopper, ensuring not to overfill - recommend half full. Before applying to surface, spray on separate fibro test board to obtain desired texture. Adjust pressure to vary texture. Spray evenly across the surface, holding the hopper approximately 600mm from the ground. Once area has been completely covered, allow to dry sufficiently to walk on.

Minimum 2 coats at total of minimum 3mm thickness required to achieve sufficient wear factor. The Dulux Avista Resurfacing System must be sealed once the surface is completely dry. Options for sealing include:

- Dulux Avista General Purpose Sealer (S/G or matt)
- Dulux Avista Extended Wear Sealer
- Dulux Avista 2 Pack Urethane
- Dulux Avista Polyaspartic Sealer

SDS Number

SDS Link
[View SDS Link](#)

3rd Coat — Dulux Avista Polyaspartic Two Pack High Gloss

Coat Type
3rd Coat

Datasheet
AUAV00024 Dulux Avista Polyaspartic Two Pack High Gloss

Read the full Datasheet details at [Dulux Avista Polyaspartic Two Pack High Gloss](#)

Components
2

Mixing Ratio
1:1 (by volume)

Pot Life
40 minutes* (after mixing) @ 20 - 25°C

Application Methods

 **Brush**  **Roller**  **Floor Squeegee**

Flooring squeegee

	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)	12.5	5	
Wet Film Per Coat (microns)	80	200	
Dry Film Per Coat (microns)	80	200	
Recoat Time **	90 minutes	18 hours	

V.O.C. Level
20g / litre

Meets GBCA V.O.C. Requirements?
Yes
Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.

Coating Application Details

Mixing

Stir the Dulux Avista Polyaspartic Part B prior to using. Combine equal parts by volume of Dulux Avista Polyaspartic Part A and Part B and mix thoroughly in an independent container using a low speed heavy duty cordless drill and suitable spiral mixer for 1 to 1½ minutes. Mix only enough product (typically 5 - 10 litres. For Resurfacing Dilute to 10 - 20% of Dulux Avista solvent to help with penetration and aid with application. This can be applied within the working life, depending on the labour available).

Important: Once mixed the product should be poured out in ribbons onto the floor and spread out immediately using a squeegee. Holding the product in the original mixing can will lead to an exothermic reaction which will significantly reduce the working life of the material

Application

1st Coat

Following the required preparation, apply Dulux Avista Polyaspartic using 230mm or 270mm unifibre roller sleeves. Note: a squeegee may be used prior to rolling to help spread material. During the application, the roller sleeves will have to be changed as they will become tacky. After spreading out the material it is important to back roll the floor. Back rolling is done to ensure even application and will help with breaking any bubbles that may have formed from pinholes. On average a roller cover will last approximately 10 min before a replacement is required.

2nd Coat (optional)

After the first coat has become tack-free, a second coat can be applied if required. This will be after approximately 1 hour but no longer than 18 hours after application of the first coat.

At temperatures of 20 - 30°C foot traffic may be permitted after 1 to 2 hours, and light vehicular traffic after 24 hours; however, in cold weather a longer period before use may be required.

If recoating after 18 hours, the surface will require a light abrade using a 100 grit sandpaper and a solvent wipe to ensure the surface is clean for better adhesion.

Overcoating Epoxy and Flake Flooring

Dulux Avista Polyaspartic can be applied over Dulux Avista epoxy and flake flooring systems. Overcoating with Dulux Avista Polyaspartic should occur within 48 hours of the application of the base epoxy coating. Refer to Dulux Avista Decorative Flakes or Natural Stone Look Flakes Technical Data Sheet (TDS) for detailed flake application process.

SDS Number

SDS Link

[View SDS Link](#)

Coating System Notes

* Practical Spreading Rate will vary from the quoted Theoretical Spreading Rate due to factors such as method and condition of application and surface roughness.

** Recoat times are quotes for 25°C and 50% relative humidity, these may vary under different conditions.

Comments

Comments

Do not apply in temperatures below 10°C as curing time is significantly delayed. It is not advisable to apply onto very hot surfaces (greater than 40°C) as this can affect cure. Therefore, under very hot conditions it is advisable to shade the application area.

Avista's Resurfacing System is a decorative coating and cracks in the concrete base may reflect through the surface.

Disclaimer

This Specification is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Duspec+ document does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Duspec+ is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Duspec+ document, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Duspec+ document, and as recommended on the applicable Dulux Product Data Sheet and Safety Data Sheets for the relevant products (available from www.duspecplus.com.au). Climatic conditions at application time can affect Duspec+ documentation suitability and product performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Specification cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.